

**DATA SHEET**

| Property  | Value  |         | Unit   | Test method              |
|---|--------|---------|--------|--------------------------|
| Melt viscosity at 190 °C<br>Rotational viscometer | 120000 | ± 30000 | mPa s  | according to DIN 53 019  |
| Softening Point<br>Ring and ball                  | 108    | ± 4     | °C     | according to DIN EN 1427 |
| Needle penetration (100/25/5)                     | 14     | ± 3     | 0,1 mm | according to DIN EN 1426 |

**SPECIAL PROPERTIES**

VESTOPLAST® 792 is a high viscous grade of good tear strength and elongation at break.

**APPLICATION**

Raw material for the production of hot melt adhesives for the furniture industry.

Marl, December 19, 2022; This data sheet replaces all previous versions. VESTOPLAST® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

**Disclaimer**

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

**Evonik Operations GmbH**

Coating & Adhesive Resins  
Paul-Baumann-Straße 1  
45764 Marl Germany  
Phone +49 2365 49-4843  
[evonik.com/adhesive-resin](http://evonik.com/adhesive-resin)