CHROMATOCEL® B-150

ACTIVATED ALUMINA (ALUMINUM OXIDE) (CAS# 1344-28-1) CHROMATOGRAPHIC GRADE

Physical	Color	White Powder
	Moisture Content (KF)	≤ 1.2 wt%
	Net LOI, 250 – 1,000 °C	≤ 3.0 wt%
	Bulk Density	820 – 1,100 g/L
	BET Surface Area*	140 – 190 m²/g
	pH by 10% Slurry	9 – 10.5
	PSD (Sieve Analysis): PSD < 45 microns* PSD 45 – 63 microns* PSD 63 – 106 microns* PSD > 106 microns*	0 – 10% 5 – 30% 35 – 75% 10 – 45%
Availability	Shipping Point	Little Rock, Arkansas
	Packaging	1,103 lbs (500 kg) bags 110 lbs (50 kg) drums, 55 lbs (25 kg) drums 55 lbs (25 kg) bags
Application	A basic granular/powdered activated alumina (aluminum oxide) for use in chrom tography, batch extractions and decolorizations. Chromatocel can also be used a general adsorbent for impurities. Optimized particle size, surface area, pH, a	

peptides, lipids, alkaloids, and a variety of other compounds.

purity make it a particularly useful material for the separation of small molecules,

*Different specifications can be made according to customer requirements.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REP-RESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMEN-DATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice. Evonik Operations GmbH Business Line Catalysts Rodenbacher Chaussee 4 63457 Hanau Germany PHONE +49 6181 59-13399 catalysts@evonik.com www.evonik.com/catalysts

