

AP-22

ACTIVATED ALUMINA (ALUMINUM OXIDE) (CAS# 1344-28-1) REHYDRATABLE POWDER

Chemical (Volatile-free Basis)	Al ₂ O ₃	> 99 wt%
	Na ₂ O	≤ 0.5 wt%
	SiO ₂	~ 0.015 wt%
Physical	Bulk Density	~ 40 lbs/ft ³ (640 kg/m ³)
Availability	Shipping Point	Little Rock, Arkansas
	Packaging	2,000 lbs (907.2 kg) supersacks
Application	A rehydratable alumina powder that can be used as a general adsorbent and ingredient.	

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Evonik Operations GmbH

Business Line Catalysts
Rodenbacher Chaussee 4
63457 Hanau
Germany
PHONE +49 6181 59-13399
catalysts@evonik.com
www.evonik.com/catalysts

