

DRYOCEL® 848

ACTIVATED ALUMINA DESICCANT FOR GAS AND LIQUID DRYING SPHERICAL

Typical Properties

Chemical (Volatile-free Basis)	Al ₂ O ₃	93.5 %
	Na ₂ O	0.35 %
	SiO ₂	0.015 %
	LOI (250 – 1000 °C)	6.0 %
Physical	Surface Area	320 m ² /g
	Total Pore Volume	0.50 cc/g
	Adsorptive Capacity (R.H. 60 %)	22 weight %
	Abrasion Loss	0.2 weight %
	Attrition (% Retained)	99.6 weight %
	Crush Strength (5 mesh equivalent)	45 lbs (20 kg)
	Bulk Density*	47 lbs/ft ³ (753 kg/m ³)
Availability	Shipping Point	Little Rock, Arkansas
	Packaging	50 lbs (22.7 kg) sacks 2,000 lbs (907.2 kg) supersacks steel drums available

Application Spherical, uniform, dust-free desiccant for applications of gas or liquid drying. High surface area leads to optimum dehydration and strong physical characteristics result in longer life.

*Density shown reflects a typical value. Actual shipments fall within a specification range (provided upon request). Orders requiring a minimum volume fill should include a 10 % contingency if based on the "typical" value.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Evonik Operations GmbH

Business Line Catalysts
Rodenbacher Chaussee 4
63457 Hanau
Germany
PHONE +49 6181 59-13399
catalysts@evonik.com
www.evonik.com/catalysts

