

Product Data and Test Information

PROTECTOSIL® 100

WATER REPELLENT

PRODUCT DESCRIPTION

A clear, penetrating, breathable VOC compliant reactive penetrating sealer for use on concrete. The isobutylalkoxy functional silane allows for faster dry times and superior performance on high quality mix designs typical of new bridge decks. Creates a deep hydrophobic layer that prevents water and waterborne contaminants from entering the substrate and causing premature deterioration. By combining ultra-low surface tension with a tailored rate of reaction, Protectosil® 100 is able to move through the moisture boundary layer that lines the pore structure of the substrate. This permits the development of uniform gradient permeation — a consistent level of protection throughout the entire depth of penetration — allowing for longer treatment life, especially on wearing surfaces.

APPROPRITATE APPLICATIONS

For use on cast-in-place, precast, GFRC and high-strength concrete, to protect the reinforcing steel from corrosion due to the effects of water, deicing salts and other waterborne contaminants. Alleviates deterioration of concrete due to alkali-silica reactivity. For use on bridge decks where fast drying is needed to minimize lane closures. For treating heavy-traffic wearing surfaces or areas that receive high salt concentrations (piers, coastal buildings), to provide a high-performance, long-lasting chloride screen.

ADVANTAGES

Protectosil® 100 is a solvent-free, isobutylalkoxysilane. Meets VOC limits for California and other regions where limits for reactive penetrating sealers have to be less than 350 grams per liter. Protectosil® 100 penetrates deeper than traditional silane and siloxane solvent- or water-carried systems. This deeper penetration gives a long-lasting, resistance against water and chloride intrusion. Protectosil® 100's breathable system greatly reduces the amount of water that enters a substrate, thus promoting a "drying out" of the substrate. Reduces the deteriorating effects of water, such as alkali silica reactivity. By incorporating Protectosil® 100 into your integrated design, you can earn vital Leadership in Energy & Environmental Design (LEED) credits for both new and existing construction projects.

The main benefits of the product are:

- · Excellent resistance to chloride ion ingress
- 100% Moisture vapor transmission
- Mitigation of AAR & ASR deterioration
- Deep penetration into substrate
- No change in surface appearance
- No change in surface friction after application
- High resistance to alkali attack
- Long service life
- Excellent performance on wearing surfaces
- Dry time 1 hour at 70°F (21°C)
- Will not inhibit adhesion of paints and line striping

LIMITATIONS

Not intended for below-grade waterproofing. Should not be applied if the surface temperature is below 20°F (-7°C) or above 110°F (43°C), if rain is expected within 4 hours following application, or if high winds or other conditions prevent proper application. If rain has preceded the application, the surface should be allowed to dry for at least 24 hours.

TECHNICAL DATA

Protectosil® 100 is a liquid isobutyl functional silane.

Color	water white
Active Substance	100% isobutylalkoxysilane
Solvent	none
Flash point	103°F
Density	7.8 lb/gal
voc	<350 g/l

TEST DATA

NCHRP #244 Series II - Reduction in wat	er absorption	
@ 175ft²/gal		88%
NCHRP #244 Series II - Reduction in chlo	ride ion ingress	
@ 175ft²/gal		88%
NCHRP #244 Series IV - Reduction in chlo	oride ion	
@ 175ft²/gal		99%

(continued)



24 hours	0.09%	
48 hours	0.11%	
50 Days	0.34%	
ASTM C672 "Deicer Scaling"		
100 Cycles	0 rating	
(non-air-entrained concrete)		
AASHTO T259 "90 Day Salt Ponding'	1	
Non Abraded specimen		
½" to 1"	94% reduction	
ASTM D6489 "Water Absorption of G	Concrete"	
48 hours	97% reduction	
Penetration, OHD L-40	•	
Concrete 0.42 w/c ratio	³ ⁄ ₈ to ½ ir	

INSTALLATION

Generally, concrete must be allowed to cure for a minimum of 28 days, however there are instances which the cure time can be shortened. Please consult your local Protectosil® rep for the criteria needed to apply sealer before the 28 day cure time. Concrete repair and replacement must be completed prior to application of **Protectosil® 100**. Patching materials, caulking, sealing materials and traffic paint must be fully cured before applying **Protectosil® 100**.

All surfaces must be cleaned to remove all traces of dirt, dust, efflorescence, mold, salt, grease, oil, asphalt, laitance, curing compounds, paint, coatings and other foreign materials. Acceptable surface cleaning methods include shotblasting, sandblasting, waterblasting and using chemical cleaners.

Check with your Protectosil® representative to verify that surface preparation is adequate. **Protectosil® 100** should be applied using low-pressure (15 to 25 psi) pumping equipment with a wet fan type spray nozzle. Alternate methods include using a spray bar or apparatus equiped with multiple nozzle tips which will apply a uniform coat across the concrete surface. Power rollers with a 1" nap or brushes are permitted, however using these will result in additional labor and costs. Do not alter or dilute the material. Do not apply to a wet or damp substrate. A test patch should be applied to the substrate by a Protectosil® representative to verify coverage rate and application conditions.

On vertical surfaces, apply the **Protectosil® 100** in a flooding application from the bottom up, so the material runs down 6 to 8 inches below the spray pattern. Coverage rates on horizontal concrete surfaces are typically between 100 and 300 square feet per gallon depending on substrate, but the average coverage rate for most common substrates is **175** sq.ft./gallon. Your Protectosil® representative can give exact coverage rates for your particular project. Please refer to the "**Protectosil® 100** Application Instructions" for more detailed information.

Precautions: Protectosil® 100 is a combustible liquid and should be kept away from heat, sparks, open flame and other sources of ignition. Protectosil® 100 containers should be kept closed when not in use and should be stored at temperatures between 0°F and 12°F (-18°C and 50°C), away from rain and standing water. When working in an enclosed area, an air respirator should be used. Please refer to the material safety data sheet for more detailed information.

AVAILABILITY

Protectosil® 100 is available in 5-gallon pails, 51-gallon drums or 255 gallon totes. Shipped F.O.B. throughout the United States and Canada. Contact your local Protectosil® representative or your regional manager for specific cost information. You can obtain their contact information on our website, www.protectosil.com, or by calling us at 1 (800) 828-0919.

TECHNICAL SERVICE

Technical service engineers and scientists are available to answer questions about product performance, application methods and compatibility with other building materials. You can speak to one of our engineers or scientists directly by calling our toll-free number, 1 (800) 828-0919, and selecting option 1.

(continued)



MANUFACTURER

Evonik Corporation 2 Turner Place Piscataway, NJ 08854 1 (800) 828-0919 protectosil@evonik.com silanes.evonik.com/en

PROTECTOSIL® PRODUCTS ARE MANUFACTURED AT THE EVONIK CORPORATION THEODORE, ALABAMA, PLANT UNDER A QUALITY SYSTEM CERTIFIED TO ISO-9001, ISO-14001, AND ISO-50001 REQUIREMENTS.

For more information, SDS and the most updated product information, and to find your local representative, go to silanes.evonik.com/en

Protectosil® = registered trademarks of Evonik Industries This information and all technical and other advice are based on Evonik Corp's ("Evonik") present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right tomake any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS ANDWARRANTIES, WHETHER EXPRESSOR IMPLIED, AND SHALLHAVENOLIABILITY FOR MERCHANTABILITYOF THE PRODUCTOR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility and obligation to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

