

Product Information

VESTAKEEP® 4000 FC30

CARBON FIBER-REINFORCED, GRAPHITE AND PTFE-FILLED POLYETHER ETHER KETONE



VESTAKEEP® 4000 FC30 is a carbon fiber reinforced, graphite and PTFE-filled polyether ether ketone for injection molding. Parts made of this resin can be used for bearing bushing or gearbox parts due to the selflubricating effect.

The semi-crystalline polymer features superior mechanical, thermal, and chemical resistance. Parts made from VESTAKEEP® 4000 FC30 are of low flammability.

VESTAKEEP® 4000 FC30 can be processed by common injection molding machines for thermoplastics.

We recommend a melt temperature between 370°C and 380°C during the injection molding process. If temperatures exceed 380°C, toxic gases can be released. Adequate ventilation and protective equipment must be provided. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 4000 FC30 is supplied as cylindrical pellets in 25 kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may affect values.

For information about processing of VESTAKEEP® 4000 FC30, please follow the general recommendations in our brochure "VESTAKEEP® PEEK Processing Guidelines".

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM OR VISIT OUR PRODUCT AT WWW.INDUSTRIAL.VESTAKEEP.COM

Key Features

Industrial Sector

Automotive and Mobility, Industry and Engineering

Resistance to

Heat (thermal stability), Fire / burn

Processing

Injection molding, Extrusion

Additives

Carbon fibers

Delivery form

Pellets, Granules

Mechanical properties ISO

Tensile modulus

Value

12500

Unit

MPa

Test Standard

ISO 527

Tensile strength	160	MPa	ISO 527
Stress at break	160	MPa	ISO 527
Strain at break, B	2	%	ISO 527
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Type of failure	C	-	-
Charpy impact strength, -30°C	45	kJ/m ²	ISO 179/1eU
Type of failure	C	-	-
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Type of failure	C	-	-
Charpy notched impact strength, -30°C	7	kJ/m ²	ISO 179/1eA
Type of failure	C	-	-
Flexural strength, 23°C	240	MPa	ISO 178
Flexural modulus, var. temp.	10300	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
Melting temperature	340	°C	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	310	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	330	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	340	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	335	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	20	E-6/K	ISO 11359-1/-2
Melting Temperature	340	°C	ASTM D 3418

Physical properties	Value	Unit	Test Standard
Density	1450	kg/m ³	ISO 1183
Water absorption	0.4	%	Sim. to ISO 62
Moisture content	0.05	Gew.-%	ISO 15512
Density	1450	kg/m ³	ASTM D 792

Shore D hardness, 1s, annealed	83.5	-	ASTM D 2240
--------------------------------	-------------	---	-------------

Burning Behav.	Value	Unit	Test Standard
UL Yellow Card available	yes	-	-
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burnin behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Burnin behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Oxygen index	44	%	ISO 4589-1/-2
Limiting Oxygen Index	44	%	ASTM D 2863
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	900	°C	IEC 60695-2-13
Hot Wire Ignition (HWI)	4	PL-Klasse	IEC 60695-2-20
HWI - thickness tested	0.4	mm	-
Hot Wire Ignition (HWI)	2	PL-Klasse	IEC 60695-2-20
HWI - thickness tested	0.8	mm	-
Hot Wire Ignition (HWI)	1	PL-Klasse	IEC 60695-2-20
HWI - thickness tested	1.5	mm	-
Hot Wire Ignition (HWI)	1	PL-Klasse	IEC 60695-2-20
HWI - thickness tested	3.0	mm	-

Electrical properties	Value	Unit	Test Standard
Volume resistivity, V	100000	Ohm*m	IEC 62631-3-1
Surface resistivity, E	1000000	Ohm	IEC 62631-3-2

Relative permittivity, 100Hz	5.9	-	IEC 62631-2-1
Relative permittivity, 1MHz	4.9	-	IEC 62631-2-1
Dissipation factor, 100Hz	600	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
CTI, Performance Level Categories, PLC	4	class	ASTM D 3638


Rheological properties	Value	Unit	Test Standard
Melt volume-flow rate, MVR	38	cm ³ /10min	ISO 1133
Temperature	400	°C	-
Load	21.6	kg	-
Melt volume-flow rate, MVR	38	cm ³ /10min	ISO 1133
Temperature	400	°C	-
Load	21.6	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Rheological calculation properties	Value	Unit	Test Standard
Min. mold temperature	160	°C	-
Max. mold temperature	200	°C	-
Min. melt temperature	380	°C	-
Max. melt temperature	400	°C	-

Test specimen production	Value	Unit	Test Standard
Injection Molding, melt temperature	410	°C	ISO 294
Injection Molding, mold temperature	200	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294
Injection Molding, pressure at hold	120	MPa	ISO 294

Diagrams

Tensile modulus-temperature



Characteristics

Applications

Electrical and Electronical, Encapsulation

Special Characteristics

Semi-crystalline

Color

Natural color

Additives

External lubrication

Chemical Resistance

General chemical resistance

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)
- ✓ Hydrochloric Acid (36% by mass) (23°C)
- ✗ Nitric Acid (40% by mass) (23°C)
- ✓ Sulfuric Acid (5% by mass) (23°C)
- ✓ Chromic Acid solution (40% by mass) (23°C)

Bases

- ✓ Sodium Hydroxide solution (35% by mass) (23°C)
- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

Hydrocarbons

- ✓ n-Hexane (23°C)
- ✓ Toluene (23°C)
- ✓ iso-Octane (23°C)

Ketones

- ✓ Acetone (23°C)

Ethers

- ✓ Diethyl ether (23°C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ Insulating Oil (23°C)

Standard Fuels

- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✓ Ethyl Acetate (23°C)
- ✓ Hydrogen peroxide (23°C)
- ✓ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ Water (23°C)
- ✓ Deionized water (90°C)

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com