

Product Information

INFINAM® PA 6001 P**POLYAMIDE-12 POWDER FOR ADDITIVE FABRICATION PROCESSES**

INFINAM® PA 6001 P is a fine powder especially for the use in additive fabrication. It is characterized by a high toughness and softness. Our product is suitable for manufacturing of functional prototypes, manufacturing of individual units as well as serial parts. INFINAM® PA 6001 P is especially suitable for powder bed fusion technologies.

Features

- Exploitable on common systems for powder-based additive fabrication
- Easy-to-process
- High process stability
- Excellent powder flow properties
- Excellent mechanical properties
- Excellent recyclability
- Excellent surface resolution and feature detail
- Nice surface finish
- Good resistance against numerous chemicals

The features and properties presented are to be understood as typical and are intended for reference and comparison purposes only. Due to layer-wise construction and by variation of processing conditions the actual properties of components from additive processes will vary. Due to process-related deviations the user is responsible to ensure the characteristic values required for the respective use and to carry out additional application-related tests if necessary.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.INFINAM.COM

Properties of 3D printed parts acc. ISO	dry / cond	Unit	Test Standard
Tensile modulus flat X	1700 / -	MPa	ISO 527
Tensile modulus on-edge Y	1700 / -	MPa	ISO 527
Tensile modulus upright Z	1700 / -	MPa	ISO 527
Tensile strength flat X	50 / -	MPa	ISO 527
Tensile strength on-edge Y	50 / -	MPa	ISO 527
Tensile strength upright Z	50 / -	MPa	ISO 527
Nominal strain at break flat X, tB	16 / -	%	ISO 527

Nominal strain at break on-edge Y, tB	16 / -	%	ISO 527
Nominal strain at break upright Z, tB	8 / -	%	ISO 527

Thermal properties	dry / cond	Unit	Test Standard
Melting temp., DSC 1st heating, powder	187 / *	°C	ISO 11357

Powder properties	Value	Unit	Test Standard
Bulk density, powder	470	g/l	EN ISO 60
Powder flow	25	s	ISO 6186
Particle size, D(50)	58	µm	ISO 13320, DIN ISO 8130-13

Sustainability	Value	Unit	Test Standard
LCA name of certificate	INFINAM® low	-	ISO 14040, 14044
LCA certifier	TÜV Rheinland	-	ISO 14040, 14044
Blue water consumption	18.6	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	5.2	kg CO ₂ eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	5.2	kg CO ₂ eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	0.1	Annual crop eq. y	ISO 14040, 14044
GWP savings as compared to 2023 reference	-4.0	kg CO ₂ eq./kg	ISO 14040, 14044

Characteristics

Key Features, Industrial Sector

Sustainable, Industry and Engineering, 3D Printing

Key Features, Conformity

Food contact

Key Features, Sustainability

RFP (reduced foot print)

Processing

Additive manufacturing, Powder bed fusion

Key Features, Processing

3D Printing

Delivery form

Fine powder (FP)

Key Features, Delivery form

Powder

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. **EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com