

Product information

AEROSIL® 130 V

Densified hydrophilic fumed silica

Characteristic physico-chemical data

Properties and test methods	Unit	Value
Specific surface area (BET)	m²/g	105 - 155
pH value in 4% dispersion		3.7 - 4.5
Loss on drying* 2 hours at 105 °C	%	≤ 1.5
Tamped density*	g/I	арргох. 120
SiO ₂ content based on ignited material	%	> 99.8
* ex plant		

The data represents typical values (no product specification)

Registrations (substance or product components)

AEROSIL® 130 V

CAS-No.	112 945-52-5 7631-86-9	
REACH (Europe)	registered	
TSCA (USA)	registered	
DSL (Canada)	registered	
AICS (Australia)	registered	
ENCS (Japan)	registered	
IECSC (China)	registered	
KECI (Korea)	registered	

AEROSIL* 130 V is a densified hydrophilic fumed silica with a specific surface area of $130 \text{ m}^2/\text{g}$.

Applications and properties

Applications

• HCR-silicone rubber

Properties

- Reduced dust development
- Improved incorporation and handling when applying sufficient sheer forces

Safety and handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Evonik Operations, Product Safety Department, E-MAIL sds-im@evonik.com We recommend to read carefully the safety data sheet prior to the use of our product.

Packaging and storage

AEROSIL® 130 V is supplied in multiple layer 20 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROSIL® 130 V should be used within 2 years after production.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Customer Service

Europe/ Middle-East/ Africa/ Latin America Evonik Operations GmbH

Business Line Silica
PB 010-A410
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 12532
FAX +49 6181 59 712532
aerosil@evonik.com
www.silica-specialist.com

North America Evonik Corporation

Business Line Silica 299 Jefferson Road Parsippany, NJ 07054-0677 USA PHONE +1 800-233-8052 FAX +1 973-929-8502 aerosil@evonik.com www.silica-specialist.com

Asia (excluding Japan) Evonik (SEA) Pte. Ltd.

Business Line Silica
3 International Business Park
Nordic European Centre, #07-18
Singapore 609927
PHONE +65 6809-6877
FAX +65 6809-6677
aerosil@evonik.com
www.silica-specialist.com

NIPPON AEROSIL CO., LTD.

Marketing & Sales Division P.O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chrome Shinjuku-ku, Tokyo
163-0913 Japan
PHONE +81 3 3342-1789
FAX +81 3 3342-1761
infonac@evonik.com
www.aerosil.jp

Technical Service

Europe/ Middle-East/ Africa/ Latin America Evonik Operations

Business Line Silica HPC 911-221 A Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany PHONE +49 6181 59-3936 FAX +49 6181 59 4489 technical.service.aerosil@ evonik.com www.silica-specialist.com

North America Evonik Corporation

Business Line Silica
2 Turner Place
Piscataway, NJ 08855-0365
USA
PHONE +1 888 SILICAS
PHONE +1 732 981-5000
FAX +1 732 981-5275
technical.service.aerosil@
evonik.com
www.silica-specialist.com

Asia (excluding Japan) Evonik Specialty Chemicals (Shanghai) Co.,Ltd

55 Chundong Road Xinzhuang Industry Park Shanghai 201108 P.R. China PHONE +86 21 6119-1151 FAX +86 21 6119-1075 technical.service.aerosil@ evonik.com www.silica-specialist.com

Business Line Silica

Japan NIPPON AEROSIL CO., LTD.

Applied Technology Group 3 Mita-Cho Yokkaichi, Mie 510-0841 Japan PHONE +81 59 345-5270 FAX +81 59 346-4657 infonac@evonik.com www.aerosil.jp

