


# Product Information VISIOMER® EGDMA



# Ethyleneglycol dimethacrylate

CAS-No.: 97-90-5

## Quality on supply

Appearance: clear, colorless to yellowish liquid
Odor: ester-like

## Standard specification

		Test Method	
Reactive-ester content:	min. 99.0 %	M2-34	(GC)
Acid content:	max. 0.05 %	M4	(acid-base titr., calculated as GMAA)
Water content:	max. 0.05 %	M3	(according to K. Fischer)
Color:	max. 50	M5	(Pt-Co)
Stabilization:	$100\pm10$ ppm MEHQ	M1-9	(HPLC)



Following data are not part of the product specification but serve as benchmarks.

#### **Physical Data**

Molecular weight	198.2 g/mol		
Density	1.051 g/cm³ (20 °C)		
Refractive index	1.455 (20 °C)		
Boiling point	275 °C (965.8 hPa)		
Vapor pressure	0.01 hPa (20 °C) (OECD 104, dyn. method)		
Melting point	- 40 ℃		
Viscosity (kinematic)	3.06 mm <sup>2</sup> /s (20 °C) (DIN 51562)		
Ignition temperature	395 °C (1,018 hPa) (DIN 51794)		
Flash point	104 °C (ASTM D93 / Pensky Martens Closed Cup)		
Solubility in water	1086 mg/l (20 °C) (OECD 105)		

#### Registration

REACH	registered
included in TSCA	+

#### **General Hints**

For information about health protection and shipment see our Safety Data Sheet

### **Application**

Crosslinking agent for the free radical polymerization. Coagent for peroxide crosslinking of elastomers.

Shelf life of the standard stabilized product: 6 months at max. 30 °C from date of delivery

Ref.-No.: VISIOMER® EGDMA / VM 041-e - 11/2023

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

• registered trademark

Evonik Operations GmbH Specialty Methacrylates Kirschenallee 64293 Darmstadt Germany

visiomer@evonik.com www.visiomer.com www.evonik.com

