
# **VISIOMER®**

## Product Information VISIOMER® EHMA



### 2-Ethylhexyl methacrylate

CAS-No.: 688-84-6

#### Quality on supply

| Appearance: | clear, colorless liquid |
|-------------|-------------------------|
| Odor:       | ester like              |

#### Standard specification

|                  |                      | Test Method |  |
|------------------|----------------------|-------------|--|
| Degree of purity | min. 98.00 %         | M2-16       | (GC)                                     |
| Acid content     | max. 0.010 %         | M4          | (acid-base titr.,<br>calculated as GMAA) |
| Water content    | max. 0.050 %         | M3          | (according to K. Fischer)                |
| Color            | max. 10              | M5          | (Pt-Co)                                  |
| Stabilization    | $50 \pm 10$ ppm MEHQ | M1-18       | (HPLC)                                   |

Following data are not part of the product specification but serve as benchmarks.

#### **Physical Data**

| Molecular weight         | 198.3 g/mol                                 |
|--------------------------|---|
| Density                  | 0.884 g/cm <sup>3</sup> (20 °C) (DIN 51757) |
| Refractive index         | 1.439 (20 °C)                               |
| Boiling point            | 227 °C (1,013 hPa)                          |
| Vapor pressure           | 0.065 hPa (20 °C)                           |
| Freezing temperature     | < - 50 °C                                   |
| Viscosity (kinematic)    | 2.12 mm²/s (20 °C) (DIN 51562)              |
| Autoignition temperature | 250 ℃                                       |
| Flash point              | approx. 97 °C (Closed Cup) (DIN 51755)      |
| Solubility in water      | 3.10 mg/l at 20 °C (OECD 105)               |
|                          |   |

#### Registration

| REACH            | registered |
|------------------|------------|
| included in TSCA | +          |

#### **General Hints**

For information about health protection and shipment see our Safety Data Sheet

#### **Application**

Copolymerization in emulsion and solution. Used as internal plasticizer. Also used in oil additives. Used in the leather, textile, paint and paper industries.

Shelf life of the standard stabilized product: 6 months at max. 30 °C from date of delivery

Ref.-No.: VISIOMER® EHMA / AM 007-e - 03/2015

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

registered trademark

Evonik Operations GmbH Specialty Methacrylates Kirschenallee 64293 Darmstadt Germany

visiomer@evonik.com www.visiomer.com www.evonik.com

