

Technical Information

KOSMOS® MB 19

Description

KOSMOS® MB 19 is a standard bismuth carboxylate catalyst. It can be used to produce 2K polyurethane elastomers, sealants, coatings or adhesives. Reaction parameters like gel time and tack free time are less depending on residual moisture than with DABCO® MB 20.

Key performance benefits

- Low toxicity
- High reactivity
- Reduced water sensitivity

Typical properties*

Appearance	Yellow liquid
Viscosity at 25 °C	3800 mPa · s
Density at 25 °C	1.15 g/cm ³
Calculated OH number	n.a.**

* For actual ranges, please refer to the Certificate of Analysis (CoA) / Sales Specification. | ** n.a. = not applicable

Application

KOSMOS® MB 19 is recommended to be used in water free polyol blends. To maximize shelf life, it is recommended to use molecular sieves or oxazolines to remove residual moisture.

Storage recommendations

- Shelf life: minimum 12 months. For exact date of expiration, please consider CoA.
- Storage conditions: dry and cool place in factory-packed containers.
- Optimum storage temperature: 10 to 30 °C.

Safety instructions

Please consult the Safety Data Sheet for summary of product hazards, personal protective measures, and emergency release procedures.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Evonik Operations GmbH

Rellinghauser Straße 1-11
45128 Essen, Germany
Phone: +49 201 173 3006
Email: polyurethane@evonik.com



For any further information, contact either your regional sales or technical support or visit our customer portal explorepu.evonik.com.