

Product Information

Dynasylan® AMEO-T

proprietary composition of primary and secondary aminofunctional silanes

CAS NUMBER

919-30-2 & 13497-18-2

PRODUCT DESCRIPTION

Dynasylan® AMEO-T is a blend of primary and secondary aminofunctional silanes.

The blend contains more than 90 wt% of 3-aminopropyltriethoxysilane and up to 10% Bis-(triethoxysilylpropyl) amine. The blend possesses silanes having reactive primary and secondary amino groups as well as hydrolyzable ethoxysilyl group. The dual nature of this reactivity allows Dynasylan® AMEO-T to bind chemically to both inorganic materials (e.g. glass, metals and fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers) thus functioning as an adhesion promoter, a surface modifier and a reactive reagent.

Dynasylan® AMEO-T is a yellowish liquid with an amine-like odor. It is soluble in alcohols as well as aliphatic or aromatic hydrocarbons.

Typical Properties

Property	Unit	Value
Boiling Point, min. DIN 51356, range	°C	245
Density (20 °C) DIN 51757	g/cm ³	~0.95
Flash Point, min. DIN EN ISO 2719	°C	88
Refractive Index (20,D) DIN 51423		1.425
Viscosity (20 °C) DIN 53015	mPa·s	~2

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dynasylan® AMEO-T may be used as a constituent of aqueous sizes, neat, or added to a resin or polymer as a modifier.

Examples are:

- glass fiber/glass fabric composites: as a finish or size constituent
- mineral fiber insulating materials and abrasives: as an additive to phenolic resin binders
- foundry resins: as an additive to phenolic, furanic and melaminic resins
- sealants and adhesives: as a primer or additive and for chemical modification
- mineral-filled polymers or HFFR cables: for pretreatment of fillers and pigments
- paints and coatings: as an additive and primer for improving adhesion to the substrate.
- as a primer for glass and metal surfaces.

Dynasylan® AMEO-T may react with a variety of inorganic substrates and modify their surfaces. Examples of suitable inorganic substrates are glass, glass fibers, glass wool, mineral wool, silicic acid, quartz, cristobalite, wollastonite, mica as well as aluminum trihydrate, magnesium dihydrate, kaolin, talc, other silicate fillers, metal oxides and metals.

Dynasylan® AMEO-T may react with a variety of organic resins and polymers and form silane-functionalized materials. Examples of suitable organic resins and polymers are epoxy, phenolic, furanic and melaminic resins, polyurethanes, PA, PBT, PC, EVA, modified PP, PVB, PVAC, PVC, PS, polyester, acrylates and silicones.

Dynasylan® AMEO-T can undergo reactions with ketone or ester solvents. Silane or silanized substrates can react with carbon dioxide to form the corresponding carbonates and/or carbamates.

Addition reactions with suitable monomeric or polymeric compounds (e.g. isocyanates, epoxides, etc.) are established and state of the art.

BENEFITS & ADVANTAGES

The most important product properties which can be improved by the use of Dynasylan® AMEO-T are:

- adhesion at the interphase between organic and inorganic materials
- mechanical properties, for example flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance
- electrical properties like dielectric constants or volume resistivity.

The most important processing properties which can be improved by the use of Dynasylan® AMEO-T are:

- filler dispersion
- filler loading
- rheological behavior like reduction of viscosity.

HANDLING & PROCESSING

The hydrolysis of Dynasylan® AMEO-T takes place autocatalytically. Slight turbidities may occur over time.

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://www.evonik.com/en/company/businesslines/se.html> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® AMEO-T is supplied in 25 kg cans, 190 kg drums and 900 kg IBC's.

STORAGE

Local regulations have to be followed and applied.

From technical point of view a storage between 4°C and 40°C is beneficial.

The material is stable as long as not exposed to air or moisture.

SHELF LIFE

In originally unopened containers Dynasylan® AMEO-T has a shelf life of at least 12 months from delivery.

Registration Listings

Registry	Status
Australia (AIIC)	Yes
Canada (DSL)	Yes
China (IECSC)	Yes
EU (EINECS/ELINCS)	Yes
UK (UK-REACH)	Yes
Japan (ENCS)	Yes
South Korea (KECL)	Yes
Philippines (PICCS)	Yes
USA (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects