

Dynasylan® DAMO

N-2-Aminoethyl-3-aminopropyltrimethoxysilane

Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 1.03	g/cm ³	DIN 51757
Refractive index n(20,D)	approx. 1.447	-	DIN 51423
Viscosity (20 °C / 68 °F)	approx. 6	mPa.s	DIN 53015
Boiling point (20 hPa)	140	°C	DIN 51356
Flash point	approx. 136	°C	DIN 51758

Registrations

Dynasylan® DAMO

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
REACH (Europe)	Registered

Dynasylan® DAMO is a diamino-functional silane which acts as an adhesion promoter between inorganic materials (for example glass, metals and fillers) and organic polymers (thermosets, thermoplastics and elastomers) and as a surface modifier.

Dynasylan® DAMO is a colourless to slightly yellowish liquid with an amine-like odour which is soluble in alcohols and aliphatic as well as aromatic hydrocarbons.

Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasylan® DAMO is supplied in 25 kg, 200 kg drums and 950 kg IBC containers.

In the unopened container Dynasylan® DAMO has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasylan® DAMO is an important ingredient in many applications.

Examples are:

- glass fibre/glass fabric composites: as size constituent or finish
- glass and metal primers
- sealants and adhesives: as primer or additive
- mineral-filled polymers (composites): for pre-treatment of fillers and pigments or as additive
- paints and coatings: as additive and primer for improving adhesion to the substrate.

The most important effects which can be achieved using Dynasylan® DAMO are:

improvement in product properties, such as

- flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

improvement in processing properties, such as

- adhesion

Reactivity

Dynasylan® DAMO is a bifunctional organic compound in which the silicon-functional methoxy-groups hydrolyze in the presence of water to form reactive silanols, which can be bonded to an inorganic substrate; the organophilic diamino group can interact with a suitable polymer.

The hydrolysis of Dynasylan® DAMO takes place autocatalytically. The pH of the hydrolysate is about 10-11. For longer stability of the hydrolysate a pH of 4 is recommended. Examples of particularly suitable inorganic substrates are glass or glass fibres. Examples of suitable polymers are PA, PBT, PC, EVA, modified PP, PVAC, PVC, acrylates and silicones.

Dynasylan® DAMO can undergo reactions with ketones or esters as solvents. The silane or silanized substrates can react with carbon dioxide to form the corresponding carbonates resp. carbamates. Product modifications are possible through addition reactions with suitable monomeric or polymeric compounds (for example isocyanates, epoxides, etc.).

Processing

For substrate pretreatments, for example as a primer (as an approximately 0.5-10 percent solution), Dynasylan® DAMO can advantageously be employed in organic solvents, such as alcohols and constituent of aqueous sizes or solutions. It may also be used as a pure substance or added to the polymer as an additive.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa**Evonik Operations GmbH**

Silanes Business Line
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik (SEA) Pte. Ltd.**

Silanes Business Line
3 Internatioanl Business Park
#07-18, Nordic European
Centre
Singapore 609927
PHONE +65 6809 6906
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Japan Co. Ltd**

Silanes Business Line
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America**Evonik Corporation**

Silanes Business Line
299 Jefferson Road
Parsippany, NJ 07054
USA
PHONE (TOLL FREE) +1 800 237 67
45
PHONE +1 973 929 8513
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Silanes Business Line
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik India Pvt. Ltd.**

Silanes Business Line
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America**Silbond Corporation**

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 732 981 5004
FAX +1 732 981 5275
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Korea Ltd.**

Silanes Business Line
3F (Nongshim Sungmookwan
B/D)
112 Yeouidaebang-Ro
Dongjak-Gu
Seoul, 07057
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Region Central and South America**Evonik Brasil Ltda.**

Silanes Business Line
Rua Arquiteto Olavo Redig de Campos,
105
Torre A - 04711-904 São Paulo- SP
Brazil
PHONE +55 11 3146 9627
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Taiwan Ltd.**

Silanes Business Line
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242 #247
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com