

Dynasylan® HYDROSIL 2627

Aqueous oligomeric aminoalkylfunctional silane hydrolysate

Technical data

Properties and test methods	Value	Unit	Method
Amine content as NH ₂	2.0 - 2.5	wt.-%	SAA 1078
Color	< = 40	mg Pt-Co/l	ISO 6271
Content of solids	19 - 21	wt.-%	DIN-38409-H1-1
Density (20 °C)	1.0 - 1.1	g/cm ³	DIN 51757
Flash point	> = 95	°C	DIN EN 22719
pH (20 °C)	10.0 - 11.4	-	DIN 19268
Viscosity (20 °C)	< 10	mPa·s	DIN 53015

Registrations

Dynasylan® HYDROSIL 2627

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	*
PICCS (Philippines):	*
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	No
ECL (South Korea):	No
REACH (Europe)	Exempted
* =available on request	

Dynasylan® HYDROSIL 2627 provides the producer of high-performance laminate materials with an adhesion promoter between inorganic materials (glass, minerals and metals) and organic polymers (thermosets, thermoplastics and elastomers).

Dynasylan® HYDROSIL 2627 is a clear to slightly yellowish liquid. The following advantages are obtained over solution conventional organofunctional silanes:

- Increased product and processing reliability: no liberation of flammable organic constituents flash point > = 95°C
- Process flexibility: processing possible at elevated temperatures and in the vicinity of ignition sources or static charge
- Applicational advantage: in polymer systems based on water as the solvent
- Environmental protection: hydrolysis does not result in liberation of volatile organic substances

Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasylan® HYDROSIL 2627 is supplied in 25 kg PE cans, 211 kg drums and 1.000 kg IBC.

It is recommended to store Dynasylan® HYDROSIL 2627 above 4°C.

Dynasylan® HYDROSIL 2627 has a shelf life of minimum 12 months from delivery in an originally sealed drum or IBC.

Properties and applications

Dynasylan® HYDROSIL 2627 is an organosilicon compound based on water as the solvent and contains no volatile organic constituents.

Applications:

- Surface treatment of minerals
- Glass fibre reinforcement
- Priming of glass and metal
- Surface modifier for organic materials
- Additive for water-borne polymer systems

Depending on the area of application a concentration of active compound of approx. 0.5-5% may be employed. As a consequence, Dynasylan® HYDROSIL 2627 can be simply diluted with distilled water.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa**Evonik Operations GmbH**

Silanes Business Line
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik (SEA) Pte. Ltd.**

Silanes Business Line
3 Internatioanl Business Park
#07-18, Nordic European
Centre
Singapore 609927
PHONE +65 6809 6906
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Japan Co. Ltd**

Silanes Business Line
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America**Evonik Corporation**

Silanes Business Line
299 Jefferson Road
Parsippany, NJ 07054
USA
PHONE (TOLL FREE) +1 800 237 67
45
PHONE +1 973 929 8513
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Silanes Business Line
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik India Pvt. Ltd.**

Silanes Business Line
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America**Silbond Corporation**

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 732 981 5004
FAX +1 732 981 5275
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Korea Ltd.**

Silanes Business Line
3F (Nongshim Sungmookwan
B/D)
112 Yeouidaebang-Ro
Dongjak-Gu
Seoul, 07057
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Region Central and South America**Evonik Brasil Ltda.**

Silanes Business Line
Rua Arquiteto Olavo Redig de Campos,
105
Torre A - 04711-904 São Paulo- SP
Brazil
PHONE +55 11 3146 9627
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Taiwan Ltd.**

Silanes Business Line
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242 #247
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com