

# Dynasytan® TRIAMO

## Triamino-functional propyltrimethoxysilane

### Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C/ 68 °F)	approx. 1.03	g/cm <sup>3</sup>	DIN 51757
Refractive index n (20,D)	approx. 1.46	-	DIN 51423
Viscosity (20 °C/ 68 °F)	approx. 20	mPa·s / cSt	DIN 53015
Boiling point (2.7 hPa / 2 torr)	approx. 114-168	°C/ °F	DIN 51356
Flash point	approx. 137/302	°C/ °F	EN 22719

### Registrations

#### Dynasytan® TRIAMO

EINECS/ELINCS (EU); REACH (Europe)	Yes; Registered
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
TCCL (South Korea):	Yes
Switzerland	Yes
ECS (Taiwan)	Yes
KKDIK (Turkey)	Yes

Dynasytan® TRIAMO is an organofunctional silane possessing three reactive amino groups and a hydrolyzable trimethoxysilyl group.

The dual nature of its reactivity allows Dynasytan® TRIAMO to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers) thus functioning as an adhesion promoter and surface modifier. Dynasytan® TRIAMO is a clear, light to dark yellow liquid with a slight amine-like odor. It is soluble in alcohols, ketones, esters and aliphatic and aromatic hydrocarbon solvents.

### Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasytan® TRIAMO is supplied in 25 and 200 kg drums.

In unopened container Dynasytan® TRIAMO has a shelf life of min. 12 months from delivery.

## Properties and applications

Dynasylan® TRIAMO is used in applications such as:

- PVC-pastisols as an additive (ca. 0.5-1%) to improve adhesion between PVC and metals
- Foundry resins:

Important product effects that can be achieved through the use of Dynasylan® TRIAMO include:

- improved adhesion
- improved moisture and corrosion resistance

## Reactivity

In the presence of water, the methoxy (Si-OCH<sub>3</sub>) groups of Dynasylan® TRIAMO hydrolyze to form reactive silanol (Si-OH) groups which can bond to a variety of inorganic substrates.

The amine groups of Dynasylan® TRIAMO can react with a suitable polymer.

Dynasylan® TRIAMO may be used with PVC and silicones.

## Processing

Dynasylan® TRIAMO may be added to polymer matrix as an additive.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa**

**Evonik Operations GmbH**

Silanes Business Line  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Silanes Business Line  
3 Internatioanl Business Park  
#07-18, Nordic European  
Centre  
Singapore 609927  
PHONE +65 6809 6906  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Silanes Business Line  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Evonik Corporation**

Silanes Business Line  
299 Jefferson Road  
Parsippany, NJ 07054  
USA  
PHONE (TOLL FREE) +1 800 237 67  
45  
PHONE +1 973 929 8513  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Specialty  
Chemicals (Shanghai) Co. Ltd.**

Silanes Business Line  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Silanes Business Line  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 732 981 5004  
FAX +1 732 981 5275  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Silanes Business Line  
3F (Nongshim Sungmookwan  
B/D)  
112 Yeouidaebang-Ro  
Dongjak-Gu  
Seoul, 07057  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Region Central and South America**

**Evonik Brasil Ltda.**

Silanes Business Line  
Rua Arquiteto Olavo Redig de Campos,  
105  
Torre A - 04711-904 São Paulo- SP  
Brazil  
PHONE +55 11 3146 9627  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Silanes Business Line  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242 #247  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com