

ADHESION PROMOTERS FOR PVC-PLASTISOLS



Product	Benefits					Applications		
	Low Temperature Cure	Rheological Properties	Low Viscosity	Colour Stability	Sag Resistance	Underbody Coatings	Visible Sealers	Anti-chip Primers
Nourybond® 272		+		+		++		
Nourybond® 276	++	++		++		+	++	++
Nourybond® 316		+				++		++
Nourybond® 350		+	++	+	++	++		+
Nourybond® 356		+	+		+	++		

- ++ Best Choice
- + Alternative Use

Product	Properties			
	Colour Max (Gardner)	Amine Value (mgKOH/g)	Viscosity (Pa.s@25°C)	Use level (PHR)
Nourybond® 272	10	185–200	15–35	1–4
Nourybond® 276	10	110–130	9–28	1–2
Nourybond® 316	14	260–310	1–2 (75°C)	0.5–2
Nourybond® 350	10	130–170	0.5–2 (75°C)	1–3
Nourybond® 356	12	185–200	1–4.5	0.5–2

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

* is a registered trademark of EVONIK INDUSTRIES AG or one of its subsidiaries.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Straße 1
45764 Marl | Germany

Technical Information:

www.evonik.com/crosslinkers-construction

Samples: APCSE@evonik.com

Regional Contact:

www.evonik.com/crosslinkers-contacts