

Dynasylan® SIVO 110

SIVO® SOL Technology for coating systems

Technical data

Properties and test methods	Value	Unit	Method
Flash Point	> 95	°C	EN 22719
Boiling Point	approx. 96	°C	ASTM D-1120
pH-value	approx. 4.3	-	DIN 19268
Solid content	approx. 35	%	3g / 2h 105 °C
Density	approx. 1.14	g/cm ³	DIN 51757
Viscosity	approx. 7	mPa.s	DIN 53015

Registrations

Dynasylan® SIVO 110

DSL/NDSL (Canada):	No
PICCS (Philippines):	No
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	*
ECL (South Korea):	No
EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
* = information on request	

Dynasylan® SIVO 110 is a multifunctional, basically VOC-free, water-borne sol-gel system.

It is composed of organofunctional silanes and functionalized, nanoscale SiO₂ particles. Dynasylan® SIVO 110 is an opaque to milky, colorless to slightly yellow, low viscous liquid. Dynasylan® SIVO 110 can be diluted in water and a variety of common organic solvents. Besides reactive silanol groups it also contains organic functionalities based on Si-bonded epoxy groups.

Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasylan® SIVO 110 is supplied in 25 kg PE drums, 200 kg PE-inlined steel drums and 1.000 kg IBC containers.

Due to its water content Dynasylan® SIVO 110 must be stored above freezing temperature. Storage temperatures must not exceed +40 °C.

In original sealed containers Dynasylan® SIVO 110 has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasytan® SIVO 110 is suited as binder component in temperature crosslinking sol-gel coatings and sol-gel - based hybrid coatings. Dynasytan® SIVO 110 coatings boast of:

- high hardness ("Bleistifhärte" up to 5H, depending on formulation)
- excellent scratch and mar resistance
- superior stability in boiling water (Gt0 upon 2 h treatment in water at 100 °C)
- very good adhesion on various substrates
- very good adhesion towards organic top coats (e.g. epoxies)
- sound flexibility ("Dornbiegeprüfung" according to DIN EN ISO 1519: 2 mm)
- very low thickness of formed layers (recommendation: dry layer of < 2 µm)
- excellent resistance against solvents and other chemicals

Recommended areas of application:

1. corrosion resistant primer systems
2. transparent sol-gel top coats which exhibit a temperature resistance of up to 220 °C
3. coatings comprising high hardness, which can be additionally improved by introduction of up to 20 wt.-% silica sol
4. transparent easy-to-clean sol-gel - top coats upon adding Dynasytan® SIVO 112

Dynasytan® SIVO 110 containing formulations can be sprayed, dipped or applied with a doctor blade. It is recommended to orient towards a 0.2 - 2 µm thickness of the dry layer (approx. 4 µm of a wet layer equals approx. 1 µm of the respective dry layer). Hence the total quantity to be applied on smooth substrates will amount to approx. 5g / m². Generally for spray application an aqueous dilution should be used (e.g. 20 wt.-% Dynasytan® SIVO 110, 0.06 wt.-% processing agent, 79.94 wt.-% water). Surfaces of treated substrates must be clean and free of grease and dust.

Processing

Dynasytan® SIVO 110 can be mixed with water at any proportion. Dilution in common organic solvents such as ethanol, isopropanol, butyl glycol or methoxy propanol is possible. Dynasytan® SIVO 110 can be formulated with a variety of water-thinnable binders and other auxiliary agents such as Tego® Wet 280. As of such e.g. a satisfactory compatibility with acrylate-based polymer dispersions has been achieved. Nevertheless, the final formulation must be checked towards possible incompatibilities such as phase separation or precipitation. Recommended procedures a.o. are storage or stress tests. Upon addition of acids and bases the pH value of Dynasytan® SIVO 110 can be varied between 4 and 9. These acid or alkaline additives must be selected with care as flocculation or gelation can occur in contact with certain substances. For neutralization Dynasytan® SIVO 111 is strongly recommended. For acidification phosphoric acid may be used. For achievement of easy-to-clean properties Dynasytan® SIVO 112 is highly recommended. Dynasytan® SIVO 110 must be protected against freezing temperatures!

Reactivity

Dynasytan® SIVO 110 resembles a water-borne sol-gel system which does not contain organic solvents. It does not release alcohols upon hydrolysis contrary to standard functional alkoxysilanes. Dynasytan® SIVO 110 contains a high concentration of active silanol functions. Consequently it can chemically bond to surfaces of suited substrates and achieves a high degree of crosslinking by formation of 2- and 3-dimensional siloxane networks. During curing functionalized SiO₂ nanoparticles align into a densely packed structure and are covalently incorporated into the siloxane network. This phenomenon serves as an explanation why exceptional hardness and scratch resistance can be achieved with Dynasytan® SIVO 110. Additionally a high degree of flexibility is obtained at a considerably low thickness for the formed layers.

Suited substrates: steel, stainless steel, Zn-galvanized steel, aluminum, glass. Dynasytan® SIVO 110 - based coatings exhibit a state of dryness of 5 (DIN 53150) once dried a room temperature for 20 min. Complete crosslinking (including reaction of silanol groups) will be reached at temperatures between a minimum of 150 °C and, ideally, 200 – 220 °C.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa

Evonik Operations GmbH

Silanes Business Line
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Silanes Business Line
3 Internatioanl Business Park
#07-18, Nordic European
Centre
Singapore 609927
PHONE +65 6809 6906
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Silanes Business Line
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Silanes Business Line
299 Jefferson Road
Parsippany, NJ 07054
USA
PHONE (TOLL FREE) +1 800 237 67
45
PHONE +1 973 929 8513
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

**Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Silanes Business Line
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Silanes Business Line
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 732 981 5004
FAX +1 732 981 5275
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Silanes Business Line
3F (Nongshim Sungmookwan
B/D)
112 Yeouidaebang-Ro
Dongjak-Gu
Seoul, 07057
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Region Central and South America

Evonik Brasil Ltda.

Silanes Business Line
Rua Arquiteto Olavo Redig de Campos,
105
Torre A - 04711-904 São Paulo- SP
Brazil
PHONE +55 11 3146 9627
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Silanes Business Line
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242 #247
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com