

Dynasytan® SIVO 210

Proprietary aminofunctional silane composition

Technical data

Properties and test methods	Value	Unit	Method
Boiling point (1013 hPa)	240	°C	ASTM D-1120
Content Dynasytan AMEO	35-45	wt.-%	SAA 0719
Content secondary AMINO-Silanes	55-65	wt.-%	SAA 0719
Density (20 °C)	approx. 0.97	g/cm ³	DIN 51757
Flash point	> 95	°C	DIN EN ISO 2719
pH value (20 °C / 1:1 in H ₂ O)	approx. 11	-	-
Viscosity (20 °C)	approx. 4-40	mPa·s	DIN 53015

Registrations

Dynasytan® SIVO 210

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	No
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	*
ECL (South Korea):	Yes
* = information on request	

Dynasytan® SIVO 210 is an aminofunctional silane composition which acts as an adhesion promoter between inorganic materials (for example glass, metals and fillers) and organic polymers (thermosets, thermoplastics and elastomers), as a surface modifier or as chemical modification of substances.

Dynasytan® SIVO 210 is a colorless to yellowish liquid with an amine-like odor which is soluble in alcohols, aliphatic or aromatic hydrocarbons.

Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® SIVO 210 is supplied in 25 kg pails, 180 kg drums and 900 kg IBC containers.

In originally sealed containers Dynasytan® SIVO 210 has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasylan® SIVO 210 is an important additive in many applications.

Examples are:

- metal primers
- foundry resins: as additive to phenolic, furan and melamine resins
- sealants and adhesives: as primer or additive
- mineral-filled polymers (composites) or HFFR cables: for pretreatment of fillers and pigments
- paints and coatings: as additive and primer for improving adhesion to the substrate.

The most important effects which can be achieved using Dynasylan® SIVO 210 are:

improvement in product properties, such as:

- mechanical properties, for example flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

improvement in processing properties, such as:

- adhesion
- filler dispersion
- rheological behaviour: reduction in viscosity, Newtonian behaviour
- higher filler loading

Reactivity

Dynasylan® SIVO 210 contains primary and secondary aminoalkylethoxysilanes. The components are bifunctional organic compounds in which the silicon-functional ethoxy-groups hydrolyze in the presence of water to form reactive silanols, which can be bonded to an inorganic substrate; the organophilic amino group can interact with a suitable polymer. The composition contains partly six hydrolyzable substituents in one molecule. Thus Dynasylan® SIVO 210 is exceptionally suitable to form highly crosslinked networks on and between substrates and in organic matrices.

The hydrolysis of Dynasylan® SIVO 210 in water takes place by acidic catalysis (e.g. formic or acetic acid at a pH 3). To achieve solubility in organic solvents simply add 2-4 wt.-% of water per wt.-% of Dynasylan® SIVO 210. Upon stirring for 5h the solutions are ready for use.

Examples of suitable inorganic substrates are glass, silicic acid, quartz, sand, cristobalite, wollastonite and mica; also suitable are aluminium hydroxide, kaolin, talc, other silicate fillers, metal oxides and metals.

Examples of suitable polymers are phenolic resins, furane resins, melamine resins, PA, PBT, PC, EVA, modified PP, PVB, PVAC, PVC.

The secondary amino group in Dynasylan® SIVO 210 provides high basicity at somewhat lower reactivity compared to the primary amino groups. This is of major advantage in e.g. HFFR cables where the silane is added to the polymer matrix. Homogeneous distribution and bonding/networking of Dynasylan® SIVO 210 to the inorganic filler can commence unless bonding to organic materials (e.g. polymers) will proceed.

Excellent crosslinking properties make Dynasylan® SIVO 210 a preferred component in the silylation of inorganic filler surfaces and in corrosion-resistant primer systems for metal pretreatment.

Processing

Dynasylan® SIVO 210 can advantageously be employed in organic solvents as constituent of aqueous sizes or solutions or added to the polymer as an additive. In higher concentrations (1-5 wt.-%) chemical modification can be achieved by reaction with suitable functional monomers or polymers, for example those containing epoxy groups.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa**Evonik Operations GmbH**

Silanes Business Line
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik (SEA) Pte. Ltd.**

Silanes Business Line
3 Internatioanl Business Park
#07-18, Nordic European
Centre
Singapore 609927
PHONE +65 6809 6906
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Japan Co. Ltd**

Silanes Business Line
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America**Evonik Corporation**

Silanes Business Line
299 Jefferson Road
Parsippany, NJ 07054
USA
PHONE (TOLL FREE) +1 800 237 67
45
PHONE +1 973 929 8513
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Silanes Business Line
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik India Pvt. Ltd.**

Silanes Business Line
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America**Silbond Corporation**

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 732 981 5004
FAX +1 732 981 5275
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Korea Ltd.**

Silanes Business Line
3F (Nongshim Sungmookwan
B/D)
112 Yeouidaebang-Ro
Dongjak-Gu
Seoul, 07057
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Region Central and South America**Evonik Brasil Ltda.**

Silanes Business Line
Rua Arquiteto Olavo Redig de Campos,
105
Torre A - 04711-904 São Paulo- SP
Brazil
PHONE +55 11 3146 9627
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific**Evonik Taiwan Ltd.**

Silanes Business Line
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242 #247
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com