

ZEOPOL® 25

Sodium silicate solution

Characteristic physico-chemical data*

Properties and test methods	Unit	Value
Density 20°C	g/cm ³	1.495
Solids	%	43
pH		12.5
Concentration	g/l	650
Molar ratio, SiO ₂ / Na ₂ O	-	2.5
SiO ₂	%	31
Na ₂ O	%	13
Viscosity 20°C	mPas	260

*) The given data are typical values. Specifications on request.

Certifications and Classifications

ZEOPOL® 25

CAS-No.	1344-09-8
<ul style="list-style-type: none"> Quality excellence achieved through GMPs and ISO:9001 certifications 	

ZEOPOL® 25 Sodium Silicate is a clear sodium silicate solution with unique chemical and physical properties. Due to multifunctional properties and attractive economy, ZEOPOL® Sodium Silicate is widely used in various industrial applications such as pulp peroxide bleaching, de-inking of recycled paper and production of silica based chemicals. In bleaching with hydrogen peroxide, ZEOPOL® 25 Sodium Silicate boosts pulp brightness and decreases chemical cost by preventing unintentional decomposition of hydrogen peroxide.

Benefits

- Effective stabilizer for hydrogen peroxide
- Excellent pH buffer
- Serves as corrosion inhibitor
- Effective deactivator of harmful transition metals
- Environmentally friendly bleaching solution
- Prevents pulp alkali darkening

Safety and Handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Evonik Operations, Product Safety Department, E-MAIL sds-im@evonik.com We recommend to read carefully the safety data sheet prior to the use of our product.

Packaging and storage

For details regarding our packaging options for this product, please contact your local sales representative. Please store our sodium silicate solutions at moderate temperatures in a steel or alkali stable plastic container.

Prevent from freezing. Do not store in aluminum, galvanized or other light alloy containers. Store away from acids. Keep container closed when not in use. Provide adequate ventilation when containers are open. Please keep away from incompatible metals such as aluminum, zinc, tin, or copper.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Applied Technology
Evonik Operations GmbH**
Business Line Silica
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-3536
FAX +49 6181 59-4096
ask-si@evonik.com
www.silica-specialist.com

**Europe/ Middle-East/
Africa/ Latin America
Evonik Operations GmbH**
Business Line Silica
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-8118
FAX +49 6181 59-78118
ask-si@evonik.com
www.silica-specialist.com

**North America
Evonik Corporation**
Business Line Silica
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE +1 800 233-8052
FAX +1 973 929-8502
ask-si@evonik.com
www.silica-specialist.com

**Asia-Pacific
Evonik (SEA) Pte. Ltd.**
Business Line Silica
3 International Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6 809 6877
FAX +65 6 809 6677
ask-si-asia@evonik.com
www.silica-specialist.com