

DYNACOLL® 7365

43.13.668e / 01.18

Chemical composition

Solid, partially crystalline and saturated copolyester.

Application

Manufacturing of reactive hot melt adhesives with fast setting properties.

Specification

Property	Value	Unit	Test method
Hydroxyl number	14 – 20	mg KOH/g	DIN EN ISO 4629-2
Acid number	max. 2	mg KOH/g	DIN EN ISO 2114

Typical data

Molecular weight	6500	-	from Hydroxyl number
Softening point (R + B)	63	°C	DIN ISO 4625
Melting point	57	°C	DSC
Open time	30	s	Evonik method
Viscosity at 80 °C	10	Pa s	Parallel plate

Compatibility with other DYNACOLL copolyesters (1:1 blends)

Transparent: 7110, 7111, 7130, 7131, 7150, 7230, 7231, 7250, 7255, 7320, 7321, 7330, 7331, 7340, 7360, 7361, 7362, 7363, 7380, 7381

Cloudy: -

Opaque: -

Phase separation: 7140, 7210, 7390

Form supplied

200 kg drums.

Storage Stability

When stored below 30 °C in closed containers the product remains stable for at least one year. In case of open or improperly closed containers, there is a possibility of increased moisture from the atmosphere.

Safety and Handling

Please refer to our Material Safety Data Sheet.

Reactive Hot Melt

Typical data

Reaction product from DYNACOLL 7365 with 4,4-MDI (Diphenylmethane-4,4'-diisocyanate) in a ratio OH/NCO = 1/2.2

Property	Value	Unit	Test method
Softening point (R + B)	63	°C	DIN ISO 4625
Open time	50	s	Evonik method
Setting time	15	s	Evonik method
Viscosity at 130 °C	18	Pa s	Parallel plate
Tensile strength	20	N/mm ²	DIN 53 504
Elongation at break	550	%	DIN 53 504

Evonik Operations GmbH

Paul-Baumann-Str. 1
45764 Marl
Germany
PHONE +49 2365 49-02
FAX +49 2365 49-5030

Evonik Corporation

Resource Efficiency
299 Jefferson Road
Parsippany, NJ 07054-0677, USA
PHONE +1 973 929-8000
FAX +1 973 929-8460

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108, PR China
PHONE +86 21 6119-1028
FAX +86 21 6119-1254

Email adhesives@evonik.com
www.evonik.com/adhesives-sealants
www.evonik.com/designed-polymers

Replaces leaflet 43.13.668e / 09/06 and all former issues
Marl, January 12, 2018

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.