

## DYNACOLL® 7130

43.13.638e / 08.20

### Chemical composition

Solid, saturated, amorphous copolyester.

### Application

Manufacturing of reactive hot melt adhesives with fast setting properties.

### Specification

Property	Value	Unit	Test method
Hydroxyl number	31 – 39	mg KOH/g	DIN EN ISO 4629-2
Acid number	max. 2	mg KOH/g	DIN EN ISO 2114

### Typical data

Molecular weight	3000	-	from Hydroxyl number
Softening point (R + B)	79	°C	DIN ISO 4625
Glass transition temperature	30	°C	DSC
Open time	5	s	Evonik internal method
Viscosity at 130 °C	10	Pa s	Parallel plate

### Compatibility with other DYNACOLL copolyesters (1:1 blends)

Transparent: 7110, 7111, 7131, 7140, 7150, 7210, 7230, 7231, 7250, 7255, 7320, 7321, 7330, 7331, 7340, 7360, 7361, 7365

Cloudy: -

Opaque: -

Phase separation: 7380, 7381, 7390

### Form supplied

200 kg drums.

## Storage Stability

When stored below 30 °C in closed containers the product remains stable for at least one year. In case of open or improperly closed containers, there is a possibility of increased moisture from the atmosphere.

## Safety and Handling

Please refer to our Material Safety Data Sheet.

### Reactive Hot Melt Typical data

Reaction product from DYNACOLL 7130 with 4,4-MDI (Diphenylmethane-4,4'-diisocyanate) in a ratio OH/NCO = 1/2.2

Property	Value	Unit	Test method
Softening point (R + B)	88	°C	DIN ISO 4625
Open time	1	s	Evonik internal method
Setting time	1	s	Evonik internal method
Viscosity at 130 °C	45	Pa s	Parallel plate
Tensile strength	-	N/mm <sup>2</sup>	DIN 53 504
Elongation at break	brittle	%	DIN 53 504

#### Evonik Operations GmbH

Paul-Baumann-Str. 1  
45764 Marl  
Germany  
PHONE +49 2365 49-02  
FAX +49 2365 49-5030

#### Evonik Corporation

Resource Efficiency  
299 Jefferson Road  
Parsippany, NJ 07054-0677, USA  
PHONE +1 973 929-8000  
FAX +1 973 929-8460

#### Evonik Specialty Chemicals (Shanghai) Co., Ltd.

55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108, PR China  
PHONE +86 21 6119-1028  
FAX +86 21 6119-1254

Email [adhesives@evonik.com](mailto:adhesives@evonik.com)  
[www.evonik.com/adhesives-sealants](http://www.evonik.com/adhesives-sealants)  
[www.evonik.com/designed-polymers](http://www.evonik.com/designed-polymers)

Replaces leaflet 43.13.638e / 03.17 and all former issues  
Marl, August 3, 2020

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.