

# DYNACOLL® 7210

43.13.641e / 08.20

# **Chemical composition**

Liquid, saturated copolyester.

# Application

Manufacturing of flexible reactive hot melt adhesives with low melt viscosity.

# **Specification**

Property	Value	Unit	Test method
Hydroxyl number	27 – 34	mg KOH/g	DIN EN ISO 4629-2
Acid number	max. 2	mg KOH/g	DIN EN ISO 2114

## **Typical data**

Molecular weight	3500	-	from Hydroxyl number
Softening point (R + B)	-	°C	DIN ISO 4625
Glass transition temperature	-15	°C	DSC
Open time	-	S	Evonik internal method
Viscosity at 80 °C	11	Pa s	Parallel plate

# Compatibility with other DYNACOLL copolyesters (1:1 blends)

Transparent:	7110, 7111, 7130, 7131, 7150, 7230, 7231, 7250, 7320, 7321, 7340
Cloudy:	-
Opaque:	-
Phase separation:	7140, 7255, 7321, 7330, 7331, 7360, 7361, 7365, 7380, 7381, 7390

## Form supplied

200 kg drums.

## Storage Stability

When stored below 30 °C in closed containers the product remains stable for at least one year. In case of open or improperly closed containers, there is a possibility of increased moisture from the atmosphere.

### Safety and Handling

Please refer to our Material Safety Data Sheet.

### **Reactive Hot Melt Typical data**

Reaction product from DYNACOLL 7210 with 4,4-MDI (Diphenylmethane-4,4'-diisocyanate) in a ratio OH/NCO = 1/2.2

Property	Value	Unit	Test method
Softening point (R + B)	45	°C	DIN ISO 4625
Open time	several hours	-	Evonik internal method
Setting time	several hours	-	Evonik internal method
Viscosity at 130 °C	5	Pa s	Parallel plate
Tensile strength	15	N/mm <sup>2</sup>	DIN 53 504
Elongation at break	800	%	DIN 53 504

#### **Evonik Operations GmbH**

Paul-Baumann-Str. 1 45764 Marl Germany PHONE +49 2365 49-02 Fax +49 2365 49-5030 **Evonik Corporation** 

**Resource Efficiency** 299 Jefferson Road Parsippany, NJ 07054-0677, USA Xinzhuang Industry Park PHONE +1 973 929-8000 FAX +1 973 929-8460

# **Evonik Specialty Chemicals** (Shanghai) Co., Ltd.

55, Chundong Road Shanghai, 201108, PR China PHONE +86 21 6119-1028 FAX +86 21 6119-1254

Email adhesives@evonik.com www.evonik.com/adhesives-sealants www.evonik.com/designed-polymers

Replaces leaflet 43.13.641e / 03.17 and all former issues Marl, August 3, 2020

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.