

DYNACOLL® 7230

43.13.643e / 08.20

Chemical composition

Liquid, saturated copolyester.

Application

Manufacturing reactive hot melt adhesives with low melt viscosity and high flexibility.

Specification

| 27 – 34 | mg KOH/g | | |
|---------|-----------------------|---------------------------------|--|
| | ing itori/g | DIN EN ISO 4629-2 | |
| max. 2 | mg KOH/g | DIN EN ISO 2114 | |
| | | | |
| 3500 | - | from Hydroxyl number | |
| - | °C | DIN ISO 4625 | |
| -30 | °C | DSC | |
| _ | S | Evonik internal method | |
| 10 | Pa s | Parallel plate | |
| | 3500 - -30 - | 3500 - - °C -30 °C - s | |

Compatibility with other DYNACOLL copolyesters (1:1 blends)

| Transparent: | 7110, 7111, 7130, 7131, 7140, 7150, 7210, 7231, 7250, 7255, 7320, 7321, 7330, 7331, 7340, 7360, 7361, 7365, 7390 |
|-------------------|--|
| Cloudy: | - |
| Opaque: | - |
| Phase separation: | 7380, 7381 |

Form supplied

200 kg drums.

Storage Stability

When stored below 30 °C in closed containers the product remains stable for at least one year. In case of open or improperly closed containers, there is a possibility of increased moisture from the atmosphere.

Safety and Handling

Please refer to our Material Safety Data Sheet.

Reactive Hot Melt Typical data

Reaction product from DYNACOLL 7230 with 4,4-MDI (Diphenylmethane-4,4'-diisocyanate) in a ratio OH/NCO = 1/2.2

| Property | Value | Unit | Test method |
|-------------------------|---------------|-------------------|------------------------|
| Softening point (R + B) | - | °C | DIN ISO 4625 |
| Open time | several hours | - | Evonik internal method |
| Setting time | several hours | - | Evonik internal method |
| Viscosity at 130 °C | 9 | Pa s | Parallel plate |
| Tensile strength | 15 | N/mm ² | DIN 53 504 |
| Elongation at break | 900 | % | DIN 53 504 |

| Evonik | Ope | rations | GmbH |
|---------|-----|---------|------|
| E VOTIN | Ope | adono | |

Paul-Baumann-Str. 1 45764 Marl Germany PHONE +49 2365 49-02 Fax +49 2365 49-5030 **Evonik Corporation**

Resource Efficiency 299 Jefferson Road Parsippany, NJ 07054-0677, USA Xinzhuang Industry Park PHONE +1 973 929-8000 FAX +1 973 929-8460

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

55, Chundong Road Shanghai, 201108, PR China PHONE +86 21 6119-1028 FAX +86 21 6119-1254

Email adhesives@evonik.com www.evonik.com/adhesives-sealants www.evonik.com/designed-polymers

Replaces leaflet 43.13.643e / 03.17 and all former issues Marl, August 3, 2020

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.