

DYNACOLL® S 1272

45.13.084e / 05.11

General Description

Saturated, linear copolyester, partially crystalline. Contains optical brightener.

Application

Thermoplastic hotmelt adhesives for fabrics and technical textile lamination, e.g. for clothes or automotive interiors. Direct extrusion or preparation of adhesive films, nets and webs.

Supply Form / Packaging

Granules in 25 kg paper-bags or 1000 kg bigbag.

Specification

Property	Value	Unit	Test method
Viscosity number	80 - 88	cm ³ /g	DIN 53 728
Melting point (DSC) ¹⁾	123 - 133	°C	DIN 53 765

Typical data

Glass transition temperature (DSC) ¹⁾	0	°C	DIN 53 765
Softening point (Ring & Ball)	140	°C	DIN ISO 4625
Melt flow rate 160 °C (MFR)	30	g/10 min	DIN ISO 1133 (21.6 N)
Melt viscosity 160 °C	330	Pa s	(Plate/Plate)
Open time	10	s	Degussa-method
Tensile strength	25	N/mm ²	DIN EN ISO 527-1/3
Density	1.3	g/cm ³	DIN 53 479

¹⁾ Differential scanning calorimetry

Solubility

Most solvents: practically insoluble, soluble in methylene chloride.

Storage Stability

Excluding sunlight and humidity S 1272 is stable at storage temperatures below 25 °C for at least 12 months.

Safety and Handling

Please refer to our Safety Data Sheet.

Evonik Operations GmbH

Paul-Baumann-Str. 1
45764 Marl
Germany
PHONE +49 2365 49-02
FAX +49 2365 49-5030

Evonik Corporation

Resource Efficiency
299 Jefferson Road
Parsippany, NJ 07054-0677, USA
PHONE +1 973 929-8000
FAX +1 973 929-8460

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108, PR China
PHONE +86 21 6119-1028
FAX +86 21 6119-1254

Email adhesives@evonik.com
www.evonik.com/adhesives-sealants
www.evonik.com/designed-polymers

Replaces leaflet 45.13.084e / 07.01 and all former issues
Marl, May 27, 2011

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.