

Product Information

VPS 2961

aqueous oligomeric aminoalkyl- and benzylamino-functional silane hydrolysate with enhanced temperature stability

CAS NUMBER

confidential

PRODUCT DESCRIPTION

VPS 2961 is an aqueous oligomeric multifunctional product, that contains

- reactive secondary amino groups
- antistatic cationic centers
- and reactive silanol groups.

The multifunctional nature of its reactivity enables VPS 2961 to bind and interact with inorganic and organic substrates, thus functioning as an adhesion promotor and surface modifier. VPS 2961 is a slightly yellow to darker yellow-orange liquid. It is easily dilutable in water, while pH value is already acidic and does not need specific control.

Typical Properties

Property	Unit	Value
Color Gardner, ISO 4630		< = 9.0
Density (20 °C) DIN 51757	g/cm ³	1.10-1.20
Flash Point, min. DIN EN 22719	°C	95
pH Value (20 °C) DIN 19268		2.5-4.0
Viscosity (20 °C) DIN 53015	mPa·s	≤400

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

VPS 2961 is a multifunctional organic compound in which the silanol groups can be bonded to an inorganic substrate

and the organophilic amino groups can interact with a suitable polymer or resin.

Examples of suitable inorganic substrates are:

- glass, glass fibers, glass beads and glass wool
- mineral wool
- metals
- and various fillers like quartz, wollastonite or ATH

Examples of suitable polymers or resins are:

- Thermosets like epoxy, phenolic, furanic and melaminic resins
- Thermoplastics like PA, PBT, EVA, PPS, MAPE, MAPP, PVB, acrylates
- Elastomers like silicones

VPS 2961 finds application in many industries. Advantages arise in water-based systems.

Examples are:

- as a size constituent of glass fiber/glass fabric composites or mineral wool insulating materials
- as a primer or additive for sealants and adhesives
- as a pretreatment or an additive to mineral-filled thermoplastic compounds
- as a glass and metal primer
- as a primer and/or additive for paints and varnishes to improve adhesion to the substrate

Product Composition

Product Composition	Unit	Value
Chloride (Cl) Content, max. SAA 0791	wt%	11.5
Solids Content DIN 38409-H1-1	wt%	51-55

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

VPS 2961 is an aqueous oligomeric multifunctional product, that contains

- reactive secondary amino groups
- reactive styrenic double bonds
- antistatic cationic centers
- and reactive silanol groups.

Important product effects that can be achieved through the use of VPS 2961 are:

- Improved mechanical properties: e.g. flexural strength, tensile strength, impact toughness, modulus of elasticity
- improved electrical properties: e.g. dielectric constant, specific volume resistance
- improved temperature stability at the inorganic/organic interphase (>300°C)

Important processing effects that can be achieved through the use of VPS 2961 are:

- better polymer wetting
- elongated gelation time of resins
- immediate solubility in water

Advantages that can be realized compared to conventional organoalkoxy functional silanes:

Improved workplace safety

- flash point of product is $\geq 95^{\circ}\text{C}$
- only < 1 wt.-% alcohols are liberated during processing by VPS 2961

Less complex processing parameters

- process conditions are not bound to ignition limits of the liberated alcohols
- more reliable process due to prevented steps of hydrolysis and condensation of the alkoxy silanes
- better space-time yield due to a ready to use aqueous, oligomeric product
- no additional removal or separation of the released alcohol needed

Easy application and formulation

- product can be directly mixed in water based polymer, filler or binder systems

DOSAGE

VPS 2961 may be used for substrate pretreatment, for example as a primer (approx. 1-10 wt.% solution), as a con-

stituent of an aqueous size, or neat. It can be added to an aqueous mixture or sprayed onto fillers or surfaces for application (1-2.5 actives phf).

HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Please consult your local Evonik representative to discuss exact handling (e.g. dilution, wetting, curing temperature) of VPS 2961 with a technical expert to achieve the best possible results in your application.

PACKAGING

VPS 2961 is supplied in 20 kg PE cans and 170 kg drums.

STORAGE

It is recommended to store VPS 2961 above 4°C.

VPS 2961 has a flash point $\geq 95^{\circ}\text{C}$ and can be stored and transported advantageously according to different local requirements, compared to flammable liquids (Category 2, 3 and 4), as the most established monomeric alkoxy silane materials are.

SHELF LIFE

VPS 2961 has a shelf life of at least 12 months from delivery in an originally sealed can or drum.

Registration Listings

Registry	Status
Canada (DSL)	Information on Request
China (IECSC)	Yes
EU (REACH)	Exempted
Taiwan (TCSI)	Yes
United States of America (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
evonik.click/silanes