

Product Information

DEGACRYL® HS 4151 E

Solvent-based binder for heat seal lacquers

PRODUCT DESCRIPTION

Solvent-based binder for heat seal lacquers designed for direct coating of aluminum. Along with smooth peel properties, it can be sealed with all common polar and non-polar substrates like PS, PET or PP. Its solvent composition is n-butyl acetate-free.

Typical Properties

Property	Unit	Value
Chemical Name		Organic dispersion of copolymers on methacrylic esters and olefinic basis
Density DIN EN ISO 1183-1	g/cm ³	0.90
Flash Point, min. DIN EN ISO 1523	°C	-12
Glass Transition Temperature DIN EN ISO 11357-1	°C	-51
Glass Transition Temperature DIN EN ISO 11357-1	°C	30
Molecular Weight DIN 55672-1	g/mol	300,000
Solvent		n-propyl acetate / ethyl acetate / isooctane 47.8 / 43.8 / 8.4
Viscosity Dynamic Viscosity DIN EN ISO 3219	mPa·s	500-2000
Viscosity Number DIN EN ISO 1628-1	cm ³ /g	142

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Usage as a binder for PVC-free heat seal lacquers with direct adhesion for sealing aluminum or PET film versus polypropylene, polystyrene or vinyl.

- Food packaging (e.g. easy or strong peel packaging, PVC-free packaging, foil or film lid packaging, foil to foil applications)
- Pharmaceutical packaging (e.g. push through blister, sachet packaging, easy peel packaging, foil to foil applications)

Product Composition

Product Composition	Unit	Value
Solids Content	%	39-42
DIN EN ISO 3251		

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

- excellent seal and peel properties on aluminum foil or film structures
- direct adhesion on aluminum, no need for adhesion promotor like PVC-terpolymer
- outstanding smooth peel effectwide property range: from easy opening to high sealing strength
- multi-purpose sealing capabilities to various substrates
- economical and environmental friendly packaging solutions

DOSAGE

We are pleased to send guideline formulations.

HANDLING & PROCESSING

General

Organic dispersion with the usage as binder for heat seal lacquers for sealing aluminum or primed PET film versus polypropylene, polyethylene, polystyrene, polyethylene terephthalate or vinyl.

Before processing

DEGACRYL® HS 4151 E must be stirred well, since storage can lead to phase separation. Recommendation to use complete material (full packaging size) for final heat seal lacquer formulation.

Dilutability

DEGACRYL® HS 4151 E is dilutable with esters and ketones.

Drying

After brief airing, 15 seconds at 180 °C under lab conditions.

Recommended dry film thickness of DEGACRYL® HS 4151 E is 7 g per sqm.

PACKAGING

Open top steel drums: 175 kg net

Recycable IBC with PE insert: 850 kg net

STORAGE

Stored tightly closed in a cool place.

SHELF LIFE

1 year after date of delivery under above mentioned storage conditions.

Registration Listings

Registry	Status
Australia (AIRC)	Yes
Canada (DSL)	Yes
China (IECSC)	Yes
EU (REACH) EU-REACH compliant for Evonik Operations GmbH and its affiliates as EU manufacturer/EU importer.	Yes
Japan (ENCS)	Yes
South Korea (KECL)	Yes
Mexico (INSQ)	No
New Zealand (NZIoC)	Yes
Philippines (PICCS) Pre-registration is requested for specific importer.	Yes
Taiwan (TCSI)	Yes
United States of America (TSCA) ACTIVE: Commercial Status: Active	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Coating & Adhesive Resins
Paul-Baumann-Straße 1
45764 Marl
Germany
Phone +49 2365 49-4843
[evonik.click/adhesive-resins](https://www.evonik.com/evonik.click/adhesive-resins)