### **SIPERNAT® 37**


# Outstanding Anticaking & Free-flow Agents for Food Powder




**SIPERNAT® 37,** a high performance free-flow and anti-caking agent for the food industry, designed to protect customers' product from moisture and solve the caking problems due to its high absorption capacity, small particle size, and ability to attract water. Also, high absorption capacity **SIPERNAT® 37** can easily convert sticky active ingredient oil into free flow powder. Lower dosage and easily dispersed powder. Superior anticaking performance (for high fat containing, hygroscopic powder).

## COMPARISON OF SILICA TENTATIVE PHYSICO-CHEMICAL PROPERTIES

Properties and test methods	Unit	SIPERNAT® 37 (SD02012303 PL#14)	
Specific surface area (N2) following ISO 9277	m²/g	192	
DOA absorption following ISO 19246	mI/100g	00g 280	
Particle size, d50 following ISO 13320	μm	22.3	
Loss on drying (105°, 2 h)	wt.% ≤ 7.0		
Tamped density ISO 787-11	g/L	88	




### SIPERNAT® 37: HIGH EFFICIENCY FOR SEASONING POWDER



#### **SIPERNAT® 37: ANTI-CAKING PERFORMANCE**

Temperature (45 °C) & Humidity (RH 75%) : 2 Days








0.5 wt.% SIPERNAT® 37

### SIPERNAT° 37: HIGH EFFICIENCY FOR NON-DAIRY CREAMER POWDER



### SIPERNAT® 37: HIGH EFFICIENCY FOR ANTI-CAKING PERFORMANCE





0 wt.% SIPERNAT® 37

0.3 wt.% SIPERNAT® 37

#### **SIPERNAT 37°: CARRIER PERFORMANCE**

- · Convert liquid to powder affords the easier operation
- · High and consistant carrier capability
- · Facilitate the precise dosage
- · Improve the stability of ingredient
- · Flavorless and no negative effect on flavor ingredient

#### The carrier performance of the surfactant liquid

Product	Particle size D50 / μm	DOA / ml / 100g	Carrier Capability wt.%
SIPERNAT° 37	22	280	74
Competitor product	300	235	65

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rignse is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

SIPERNAT® – reg. trademark of Evonik Industries AG and its subsidiaries.

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

Silica Business Line

55 Chundong Road, Xinzhuang, Shanghai, 201108

Hong Bing

Phone +86 21 6119-2556 E-mail bing.hong@evonik.com

ask-si@evonik.com www.evonik.com www.silica-specialist.com

