

Product information

ANCAMIDE[®] 260TN

Curing Agent

DESCRIPTION

Ancamide 260TN curing agent is a member of a series of standard reactive liquid polyamides developed specifically for the curing of epoxy resins. Ancamide 260TN is a modified version of Ancamide 260A that contains more imidazoline.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber liquid		
Color	7	Gardner	ASTM D1544-80
Viscosity @ 25°C	approx. 35,000	mPas	Brookfield, ASTM D445-83
Amine Value	approx. 350	mg KOH/g	
Density @ 25°C	0.960	g/cm ³	
Equivalent Wt/{H}	120		
Recommended Use Level	65	phr, EEW=190	Some latitude is possible

ADVANTAGES

- Improved resin compatibility
- Good chemical resistance to water and aqueous alkalis
- Compatible with a wide range of solvents

APPLICATIONS

- Epoxy resins in the formulation of coal-tar-extended coatings
- Sealants and adhesives

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Material Safety Data Sheet for Ancamide 260TN curing agent.

TYPICAL CURE SCHEDULE

- 2–7 days at ambient temperature.
- 2 hours at 60°C plus 1 hour at 100°C.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit
Gel Time [150g mix @ 25°C	270	min
Thin Film Set Time @ 25°C	10	hr

*Ancamide 260TN curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

