

## Product information

# ANCAMIDE<sup>®</sup> 501

## Curing Agent

### DESCRIPTION

Ancamide 501 is an accelerated amidoamine curing agent designed for use with liquid epoxy resin. It offers faster cure speed and improved chemical resistance over unmodified amidoamines.

### TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber Liquid		
Colour	10	Gardner	ASTM D 1544-80
Viscosity @25°C	450-800	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	520-570	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	0.99		
Equivalent	68	Wt/{H}	
Recommended use Level	35	PHR	With Bisphenol A diglycidyl ether (EEW=190)

### ADVANTAGES

- Faster cure than standard amidoamines
- Low viscosity
- Excellent bonding for construction materials, particularly concrete

### APPLICATIONS

- Trowelable flooring
- Concrete coatings and primers
- Repair mortars and patching compounds
- Concrete adhesives and grouts

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Material may crystallize or solidify upon exposure to low temperatures. Crystallized or solidified material can be utilized after melting at elevated temperatures without impacting handling or physical properties. It is recommended that the material be heated to 50-70°C while mixing continuously for 1 h. Once the solidified material has fully homogenized, it can be cooled to room temperature and utilized under normal conditions.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 501 curing agent.

## TYPICAL HANDLING PROPERTIES

Property	Value	Unit	Method
Mixed Viscosity at 25°C	3,000	mPa.s	Brookfield RVTD, Spindle 4
Gel Time (150g mix at 25°C)	40	mins	Techne GT-3 Gelation Timer
Peak Exotherm (150g mix at 25°C)	158	°C	
Time to Peak Exotherm	45	mins	
Thin Film Set Time 25°C	7.5	h	BK Drying Recorder Phase III

## TYPICAL CURE SCHEDULE

- (i) 7-14 days at ambient
- (ii) 2 days @ 25°C + 2h @ 100°C

## TYPICAL PERFORMANCE PROPERTIES

Property	Value	Unit	Method
<b>Cure Schedule (ii)</b>			
<b>Tensile Strength</b>	43	MPa	ISO 527
<b>Tensile Modulus</b>	3.1	GPa	ISO 527
<b>Flexural Strength</b>	60	MPa	ISO 178
<b>Flexural Modulus</b>	2.2	GPa	ISO 178
<b>Heat Distortion Temperature</b>	46	°C	ASTM D648
<b>Tensile Elongation at Break</b>	1.3	%	

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

#### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

#### EVONIK CORPORATION

Business Line Crosslinkers  
7001 Hamilton Boulevard  
Trexlerstown, PA 18087  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

#### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chungong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

