

# ANCAMINE<sup>®</sup> 2337S

## Curing Agent

### DESCRIPTION

Ancamine 2337S curing agent is a modified aliphatic amine designed for use as a latent curing agent for epoxy resins.

### TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Light Yellow Powder	
Melting Point	63-77	°C
Particle Size	90% ≤ 10	micron
Amine Value	260	mg KOH/g
Recommended Use Level	50	phr, EEW=190

### ADVANTAGES

- Very rapid reactivity above 70°C
- Rapid green strength development
- Excellent shelf stability in undiluted resin at elevated temperatures
- Can be used as a sole curing agent or as a DICY co-cure accelerator with Ancamine 2014AS and Ancamine 2014FG curing agents
- Good adhesion
- Easy dispersion in liquid resins

### APPLICATIONS

- One-component conduction or induction heat-cure adhesives
- Potting
- Coatings
- Hot-melt prepregs

### STORAGE LIFE

At least 6 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## HANDLING PRECAUTIONS

Refer to the Safety Data Sheet for Ancamine 2337S curing agent.

## TYPICAL CURE SCHEDULE

**40 minutes at 100°C**  
**30 minutes at 120°C**

## TYPICAL FORMULATION

Property	Value	Unit
Liquid DGEBA	100.0	
Ancamine 2337S	50.0	
Fumed Silica	2.0	

## TYPICAL HANDLING PROPERTIES\*

Property	Value	Unit
Stroke Gel Time		
@ 80°C	2.7	min
@ 120°C	<1	min
DSC Activation Temperature	70	°C
Pot Life [150g mix @ 42°C]	<1	month

## TYPICAL PERFORMANCE PROPERTIES

Property	Value	Unit
Cure Schedule 2		
Glass Transition Temperature (DSC)	70	°C
Lap Shear Strength (cold rolled steel)	12	MPa

\* Ancamine 2337S curing agent formulated with standard liquid Bisphenol- A based (DGEBA, EEW=190) epoxy resin.

## SUPPLEMENTARY DATA

### REACTIVITY

Formulations with epoxy resins and varying levels of Ancamine 2337S curing agent were prepared (Table 1) to study the reactivity by the Stroke cure method and a differential scanning calorimeter (DSC). As shown in Table 1, at lower temperatures, formulations containing higher levels of modified polyamine were more reactive. At 120 °C, the differences in the reactivity of these formulations are insignificant. At all temperatures, the reactivity of formulations containing Ancamine 2337S curing agent was significantly higher than the formulation containing Ancamine 2014FG curing agent. The DSC reactivity data shows that the heat of reaction increases as a function of the amount of Ancamine 2337S curing agent and begins to level off at 50 phr. The onset and peak temperatures of formulations containing Ancamine 2337S are significantly lower than those of the control formulation, indicating the higher reactivity of Ancamine 2337S curing agent.

TABLE 1: COMPOSITION (% BY WT)

Ingredient	I	II	III	IV	V
Liquid DGEBA (EEW=190)	100	100	100	100	100
Ancamine 2337S Curing Agent	30	40	50	60	-
Ancamine 2014FG Curing Agent	-	-	-	-	28
Fumed Silica	1	1	1	1	1
<b>Stroke Gel Time (min)</b>					
@ 80°C	4.1	3.7	2.7	2.4	15.0
@ 100°C	2.1	1.6	1.4	1.2	7.0
@ 120°C	1.0	1.0	<1.0	<1.0	1.5
<b>DSC Initial Reactivity</b>					
Onset Temperature (°C)	75	72	70	70	110
Peak Temperature (°C)	96	95	95	94	130
Heat of Reaction (J/g)	185	216	270	293	210
<b>Tg (°C)</b>					
after 30 min @ 120°C cure	45	55	70	85	70

### GLASS TRANSITION TEMPERATURE:

### GLASS TRNASITION TEMPERATURE:

Samples of cured formulations were analyzed for glass transition temperature (Tg) using DSC. The scan rate was 10K/minutes starting at 20°C. Glass transition temperatures increase with higher levels of Ancamine 2337S curing agent.

## SHEAR STRENGTH DEVELOPMENT:

To determine shear strength development, electrogalvanized steel lap coupons were bonded together with a ½" overlap and 10 mil bondline thickness. All bonded coupons were cured in an air circulated oven at 80°C, 100°C, 120°C and 140°C). Lap shears were tested at room temperature according to ASTM D1002. Figures 1 and 2 show that shear strength values increased as a function of the increasing level of Ancamine 2337S curing agent, and plateaued at 50 phr for a cure temperature above 100°C. Also, formulations containing Ancamine 2337S curing agent demonstrated higher shear strength values than the control formulation under all cure conditions. The difference in shear strength values between the formulation containing Ancamine 2337S and the control formulation was more pronounced at lower temperatures, indicating more rapid development of green strength with Ancamine 2337S curing agent.

FIGURE 1: LAP SHEAR STRENGTH VS. CURE CYCLE AT 80°C AND 100°C





FIGURE 2: LAP SHEAR STRENGTH VS. CURE CYCLE AT 120°C AND 140°C




FORMULATION SHELF STABILITY:

Twenty-four hours after mixing and degassing, the viscosity of the formulations was measured at room temperature. Thereafter, the formulations were stored at 42°C, and their viscosities were measured (after equilibrating to room temperature) every week. Figure 3 indicates that formulations containing Ancamine 2337S curing agent are shelf stable for more than 4 weeks at 42°C. However, the viscosity of the control formulation containing Ancamine 2014FG curing agent doubled in 4 weeks.



FIGURE 3: % VISCOSITY INCREASE AFTER AGING @ 4 WEEK



EFFECT OF REACTIVE DILUENTS ON FORMULATION SHELF STABILITY:

The effect of reactive diluents on the shelf stability of formulations containing epoxy resin and Ancamine 2337S curing agent were studied. Results in Table 2 indicate that formulations containing 20 parts of aliphatic glycidyl ether, cresyl glycidyl ether and diglycidyl ether of neopentyl glycol adversely affected the shelf stability at 42°C. However, the viscosity of the formulation containing 20 phr of Cardura E-10 curing agent remained unchanged after 4 weeks.

TABLE 2: COMPOSITION (% BY WT)

Ingredient	I	II	III	IV	V
Liquid DGEBA	100	80	80	80	80
Aliphatic Glycidyl Ether (Epodil® 748)	-	20	-	-	-
Cresyl Glycidyl Ether (Epodil 742)	-	-	20	-	-
Diglycidyl Ether of Neopentyl Glycol (Epodil 749)	-	-	-	20	-
Glycidyl Ether (Cardura E-10)	-	-	-	-	20
Ancamine 2337S Curing Agent	40	33	40	43	38
<b>Shelf Stability @ 42°C</b>					
% Viscosity Increase After 4 wk	40	gelled	gelled	gelled	44



## ANCAMINE 2337S AS A CO-CURE ACCELERATOR:

Ancamine 2337S can be used as a co-cure accelerator with Ancamine 2014AS or Ancamine 2014FG curing agents for DICY-based epoxy formulations.

The reactivities of the formulations shown in Table 3 were analyzed by DSC, scanning from 25°C to 280°C at a ramp rate of 10K/min.

The formulation containing Ancamine 2337S curing agent as a co-cure accelerator demonstrated two separate peaks. The first peak, with lower onset and peak temperatures, represents the reactivity of Ancamine 2337S curing agent with epoxy resin. The second peak resulted from the reaction of Ancamine 2014AS and Amicure CG-1200 dicyandiamide with epoxy resin.

TABLE 3: COMPOSITION (% BY WT)

Ingredient	I	II
Liquid DGEBA	100	100
Amicure CG-1200 Curing Agent	8	6
Ancamine 2014AS Curing Agent	6	4
Ancamine 2337S Curing Agent	-	10
<b>DSC Initial Reactivity</b>		
Onset Temperature (°C)	131	Peak 1-78 Peak 2-137
Peak Temperature (°C)	149	Peak 1-95 Peak 2-157
Heat of Reaction (J/g)	160	Peak 1-24 Peak 2-228
Green Strength Development Lap Shear Strength after 60 min @ 100 °C (MPa)	0	1.1
Glass Transition Temperature (°C) after 30 min @ 140 °C	118	121

## COMPARATIVE ANALYSIS WITH COMMERCIAL LATENT CURING AGENTS


### REACTIVITY

Reactivity with liquid epoxy resin was evaluated and compared for Ancamine 2337S and three commercial latent curing agents. Formulations (Table 4) were studied for viscosity increase as a function of time at 80°C by a Rheometrics Dynamic Analyzer. Each sample was loaded into an environmental chamber preheated to 80°C. The rate of viscosity increase was significantly greater for the formulation containing Ancamine 2337S than for the formulations containing other commercial curing agents, again indicating rapid green strength development (Figure 4).

TABLE 4: COMPOSITION (% BY WT)

Ingredient	I	II	III	IV
Liquid DGEBA	100	100	100	100
Ancamine 2337S	40	-	-	-
Latent Curing Agent A	-	25	-	-
Ancamine 2014AS	-	-	28	-
Latent Curing Agent B	-	-	-	35

FIGURE 4: VISCOSITY VS. TIME @ 60 °C






## FORMULATION SHELF STABILITY:

The formulations were also evaluated for shelf stability. The formulation containing Ancamine 2337S curing agent demonstrated acceptable shelf stability at 42°C, despite its excellent low temperature reactivity (Figure 5).

FIGURE 5: % VISCOSITY INCREASE AFTER AGING @ 4 WEEKS



## ANCAMINE 2337S IN INDUCTION HEAT-CURE FORMULATIONS

Ancamine 2337S curing agent can be used as a sole curing agent in induction heat-cure epoxy formulations and as a co-cure accelerator with Ancamine 2014AS or Ancamine 2014FG curing agent. The improved low-temperature reactivity of Ancamine 2337S curing agent allows rapid development of green strength and reduced cycle time.

The formulations (Table 5) were studied for shear strength development and environmental resistance.

## SHEAR STRENGTH DEVELOPMENT

The induction heat-cured formulations were studied for green strength development by immediately testing bonded lap shears for shear strength. The formulation containing Ancamine 2337S as a co-cure accelerator with Ancamine 2014FG curing agent demonstrated improved reactivity and adequate handling strength.

Lap shears bonded under induction heat were tested for 24 hours and after post-cure. The results are shown in Table 5.

## ENVIRONMENTAL RESISTANCE

The adhesive formulations were also tested for environmental resistance. After postcuring, lap shear samples were exposed to two aggressive environmental conditions for 30 days and then tested at ambient temperature. Results in Table 5 indicate little effect on adhesion due to environmental exposure.

TABLE 5: COMPOSITION (% BY WT)

Ingredient	I	II	III	IV	V
Liquid DGEBA (EEW=190)	100	100	100	100	100
Ancamine CG-1200 Curing Agent	8	8	-	-	-
Ancamine 2014FG Curing Agent	5	5	-	-	-
Ancamine 2337S	-	10	40	50	60
Iron Oxide	20	20	20	20	20
<b>Shear Strength Development: Lap Shear Strength (MPa) after</b>					
6 sec (1 sec ramp, 5 sec hold) @ 200°C	0	0.2	-	-	-
4 sec (1 sec ramp, 3 sec hold) @ 175°C	0	0	0.2	0.3	0.5
24 hr @ ambient temperature	-	1.8	3.3	5.3	5.7
Post-cure @ 163°C for 30 min	-	8.4	7.2	7.7	9.1
<b>Environmental Resistance: Lap Shear Strength (psi) after</b>					
30 days in water @ 55°C	-	7.8	8.2	6.5	6.9
30 days in salt spray	-	8.8	5.3	8.3	8.6

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

**Disclaimer**

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

**EVONIK OPERATIONS GMBH**

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**EVONIK CORPORATION**

Business Line Crosslinkers  
7001 Hamilton Boulevard  
Trexlerstown, PA 18087  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

**EVONIK SPECIALTY CHEMICALS  
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

