

ANCAMINE[®] 2410B75**Curing Agent****DESCRIPTION**

Ancamine 2410B75 curing agent is a 75% solids, highly monodispersed adduct of a polyamine and liquid epoxy resin cut in butanol and is designed for use in coatings and related applications.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Light yellow liquid		
Colour	2	Gardner	ASTM D 1544-80
Viscosity @ 25°C	11000	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	340	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	1.05	g/ml	
Equivalent	114	Wt/{H}	
Recommended use Level	60	PHR	With Bisphenol A diglycidyl ether (EEW=190)

ADVANTAGES

- Excellent resistance to a wide variety of aggressive chemicals
- Fast dry speed combined with a long pot life
- Low residual polyamine for reduced amine blush
- Excellent dilution profile (as a result of narrow molecular weight distribution) for easier handling and reduced VOC
- Can be used in food contact applications

APPLICATIONS

- Tank linings
- Chemically resistant high solids coatings
- Coatings for food contact
- As an accelerator for other curing agents where improved chemical resistance and dry speed are required

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2410B75 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit	Method
Thin Film Set Time @ 25°C	2	hrs	BK Drying Recorder Phase
Typical cure schedule	2- 7	days	

ANCAMINE® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

