

ANCAMINE[®] 2489**Curing Agent****DESCRIPTION**

Ancamine 2489 is a modified cycloaliphatic polyamine adduct intended for use as a room temperature curing agent for liquid epoxy resin. Ancamine 2489 has a very low viscosity which imparts low mixed viscosity in epoxy systems and reduced need for diluents. Ancamine 2489 offers fast property development. The low loading allows a 1:2 mix ratios with bisphenol F resins.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear light yellow liquid		
Colour	<2	Gardner	ASTM D 1544-80
Viscosity @ 25°C	50-125	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	345-375	mg KOH/g	Perchloric Acid Titration
Recommended use Level	44	PHR	With Bisphenol A diglycidyl ether (EEW=190)
Equivalent	83	Wt{H}	

ADVANTAGES

- Very low viscosity and mixed viscosity in epoxy systems
- Fast cure and development of properties at ambient and low temperature
- Good chemical resistance

APPLICATIONS

- Chemically resistant high solids and solvent free coatings
- Industrial flooring applications such as self-leveling floors and mortar floors
- Accelerator for other curing agents

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2489 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit	Method
Mixed Viscosity at 25°C	1,200	mPa.s	Brookfield RVTD, Spindle 4
Gel Time (150g mix at 25°C),	24	mins	Techne GT-3 Gelation Timer
Thin Film Set Time @ 25°C	3.5	h	BK Drying Recorder Phase III
Shore D 20°C 8/24 hours	75/82		DIN 53505
Shore D 10°C 8/24 hours	74/76		DIN 53505
Typical cure schedule	2-7	days	

TYPICAL PERFORMANCE PROPERTIES

Property	Value	Unit	Method
Compressive Strength	84	MPa	ISO 604
Compressive Modulus	2.0	GPa	ISO 604
Tensile Strength	59	MPa	ISO 527
Tensile Modulus	6.8	GPa	ISO 527
Flexural Strength	101	MPa	ISO 178
Flexural Modulus	3.2	GPa	ISO 178
Heat Distortion Temperature	47	°C	ASTM D648
Carbamation Test	3		Scale 1-5 (5 is best)

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

