

Product information

ANCAMINE[®] 2844

Curing Agent

DESCRIPTION

Ancamine[®] 2844 curing agent is a low viscosity high solid amine curing agent designed for use in plural component spray applications.

Ancamine[®] 2844 curing agent is highly reactive and exhibits ultra-fast cure and rapid property development at low temperature providing excellent surface appearance.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Colorless to light yellow liquid		
Colour	10	Gardner	ISO 4630
Viscosity @ 25°C	1000 - 2000	mPa.s	ISO 2555
Amine Value	460	mg KOH/g	DIN 16945
Specific Gravity @ 21°C	1.04		ISO 2811
Equivalent	70	Wt/{H}	
Recommended use Level	40	PHR	With bisphenol-A based epoxy resin (EEW=190)

ADVANTAGES

- . Ultra-fast cure and rapid property development at low temperature
- . Excellent surface appearance at low temperature and high humidity
- . Good chemical resistance

APPLICATIONS

- . Marine
- . Protective coating

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

HANDLING PRECAUTIONS

Refer to the Safety Data Sheet for Ancamine 2844 curing agent.

TYPICAL CURE SCHEDULE

1 day at ambient temperature.

TYPICAL PERFORMANCE PROPERTIES

Property	Value	Unit	Method
Gel Time	13	mins	Techne Gelation Timer, 150 g mix
Thin Film Set Time @ 23 °C	1/2	h	ASTM D 5895 - Dry hard time
Thin Film Set Time @ 5°C	3/4.5	h	ASTM D 5895 – Dry hard time
PersoZ Hardness after 1 / 7 days	200/350	s	ISO 1522
Carbamation Resistance @ 23 °C	5		ISO 2812
Carbamation Resistance @ 5°C	5		ISO 2812

*With bisphenol-A based epoxy resin (EEW=190)

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

