

NOURYBOND[®] 316

Adhesion Promoter

DESCRIPTION

Nourybond 316 adhesion promoter is a modified polyamidoamine PVC plastisol adhesion promoter intended for use in automotive sealants, underbody coatings and anti-chip primers. It is designed to provide adhesion to electrode deposition primers used in the manufacture of automobiles and larger vehicles such as trucks and buses.

This highly effective adhesion promoter requires low usage level at 0.5-2.0%.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear, amber liquid		
Colour	≤14	Gardner	ASTM D 1544-80
Viscosity @ 75°C	1.0-2.0	Pa.s	Brookfield RVT, Spindle 4
Amine Value	260-310	mg KOH/g	Perchloric acid titration
Recommended Use Level	0.5-2.0	wt %	In PVC plastisol formulation

ADVANTAGES

- Allows for 130°C cure
- Highly efficient / low loading
- Good rheology property profile
- Provides adhesion to a wide variety of automotive electro deposition primers

APPLICATIONS

- Underbody coating and sealer
- Non Visible seam sealer
- Anti-chip primers

SHELF LIFE

At least 24 month from the date of manufacture in the original sealed drum at cool and dry place

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Nourybond 316 adhesion promoter.

TYPICAL CURE SCHEDULE

30 min @ 130°C

Nourybond® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

