

## Product information

# VESTANAT<sup>®</sup> B 1044 E

(PRELIMINARY)

## GENERAL DESCRIPTION

VESTANAT<sup>®</sup> B 1044 E is a blocked cycloaliphatic polyisocyanate. It is supplied as a 65 % by wt. solution in n-butyl acetate.

## SPECIFICATION

Property	Value	Unit	Test method*
Non volatile matter	65 ± 1	% by wt.	DIN EN ISO 3251 (75 min. at 65°C)
Viscosity at 23 °C	2400 ± 1600	m Pas	DIN EN ISO 3219

## TYPICAL DATA

Property	Value	Unit	Test method
Free NCO content	≤ 0.4	% by wt.	DIN EN ISO 11 909 / ASTM D 2572
NCO equivalent (as supplied)	approx. 630	g/equ.	
Splitting temperature	approx. 110	°C	–
Colour number (Gardner)	≤ 2	–	DIN EN ISO 4630 / ASTM D 1544
Flash point (closed cup)	26	°C	DIN EN ISO 2719
Vapour pressure at 50 °C	≤ 50	hPa	–

## PROPERTIES AND APPLICATIONS

Blocked polyisocyanate for the combination with suitable hydroxylated resins, like polyester, acrylic and alkyd resins.

VESTANAT<sup>®</sup> B 1044 E enables the formulation of heat curing PUR coatings for curing temperatures of ≥ 110 °C.

Due to the high reactivity of VESTANAT<sup>®</sup> B 1044 E an increased viscosity of the formulated paint can be noted during storage.

## STORAGE

VESTANAT® B 1044 E can be stored in unopened containers for at least one year without loss of quality in accordance with the above specifications.

VESTANAT® B 1044 E is supplied in 25 kg non returnable cans and in 200 kg net drums.

## SAFETY AND HANDLING

Please refer to our Material Safety Data Sheet.

Marl, January 10, 2024; This data sheet replaces all former issues.

VESTANAT® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

For contact in your country, please visit: [www.evonik.com/crosslinkers-contact](http://www.evonik.com/crosslinkers-contact)

### EVONIK CORPORATION

Business Line Crosslinkers  
299 Jefferson Road,  
Parsippany, NJ 07054-0677  
USA

### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

