

VESTANAT[®] B 1370**GENERAL DESCRIPTION**

VESTANAT B 1370 is a blocked, cycloaliphatic polyisocyanate. It is supplied as a solution of 60 % in n-butyl-acetate/xylene.

SPECIFICATION

Property	Value	Unit	Test method
Solids content	60 ± 1	% by wt.	ISO 3251 (1.5 h 110 °C, < 2 hPa)
Viscosity at 23 °C	2.6 ± 0.5	Pa·s	ISO 3219

TYPICAL DATA

Property	Value	Unit	Test method
Solvents	-	n-butylacetate/ xylene (3 : 5)	-
Free NCO content	< 0.1	% by wt.	ISO 11 909 / ASTM D 2572
Latent NCO content	approx. 8	% by wt.	ISO 11 909 (modified)
Splitting temperature	130	°C	-
Density (25 °C)	1.03	g/cm ³	DIN 51 757 / ASTM D 2111
Colour (APHA)	≤ 150	-	DIN/ISO 6271
Flash point (closed cup)	28	°C	DIN 53 213 / ISO 1516
Vapour pressure at 50 °C	approx. 10	hPa	-

PROPERTIES AND APPLICATIONS

VESTANAT B 1370 is a blocked polyisocyanate for crosslinking of suitable hydroxylated resins, like polyester, acrylic and alkyd resins.

VESTANAT B 1370 may be classified as an exceptionally light fast and weathering resistant resin. It is characterized by an excellent balance of reactivity and storage stability of the formulated paint.

Typical fields of application are:

- Exterior Can Coatings (overprint varnishes, printing inks, basecoats) in combination with polyesters of the DYNAPOL® LH-range characterized by good adhesion, colour stability and sterilisation resistance.
- Coil Coatings for exterior applications
- Automotive OEM topcoats with improved acid etch resistance
- Stone chip resistant automotive OEM primer/surfacer

In principle it is possible to formulate PUR stoving paints which cure at temperatures ³ 130 °C. It is recommended to use tin catalysts, e.g. dibutyl tin dilaurate (DBTDL), in concentrations of 0.1 – 0.5 % by weight calculated on the resin.

The properties of the cured coatings are decisively determined by the polyols employed. Due to the fact that VESTANAT B 1370 imparts hard segments into a coating, it might be necessary to use additionally flexibilizing polyols, recommendations are available on request.

TABLE OF CURING CONDITIONS

In table 1 curing conditions determined by using 0.8 mm thick aluminum panels placed in a circulating air oven are listed. Stated temperatures refer to those of the circulating air in the stoving oven.

TAB. 1: CURING CONDITIONS OF 1K PUR SYSTEMS

System	Stoving times in minutes at an oven temperature of				
	130 °C	140 °C	150 °C	160 °C	180 °C
(with 0.5 % DBTDL on resin)					
VESTANAT® B 1370 /polyester (2.5 – 4 % OH)	50	30	15	10	5
VESTANAT® B 1370 /acrylic polyol (2.5 – 4 % OH)	30	15	10	8	4

STORAGE AND PACKAGING

VESTANAT® B 1370 can be stored in unopened containers for at least one year without loss of quality in accordance with the above specification.

VESTANAT® B 1370 is supplied in non returnable 25 kg net cans and in non returnable 200 kg net drums.

SAFETY AND HANDLING

Please refer to our Material Safety Data Sheet.

Marl, June 10, 2018; This data sheet replaces all former issues.

VESTANAT® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION

Business Line Crosslinkers
299 Jefferson Road,
Parsippany, NJ 07054-0677
USA

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

