

Product Information

DYNOCEL® 643

Dehydration of vapor or liquid phase hydrocarbons.

PRODUCT DESCRIPTION

Dynocel 643 is used to dehydrate vapor phase and liquid phase olefinic hydrocarbons. Dynocel 643 does not require a preload step.

Typical Properties

Property	Unit	Value
Bulk Density	kg/m ³	688-720
Particle Size 3.0 mm	*8 mesh	4
Particle Size 1.5 mm	*12 mesh	8
Product Dimensions Diameter		3 Å
Side Crush Strength		16 lbs (4 x 8 mesh); 10 lbs (8 x 12 mesh)

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dehydration of vapor or liquid phase hydrocarbons.

Product Composition

Product Composition	Unit	Value
Moisture Content	wt%	≤1.5

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

Dynocel 643 does not require a preload step prior to use in olefinic hydrocarbon streams.

PACKAGING

- 1000 kg (2205-lb) supersacks
- steel drums available

STORAGE

The material should be stored in its original container and in a dry, covered location protected from the ambient environment.

SHELF LIFE

5 years in original packaging stored in a dry, covered location

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Catalysts
Rodenbacher Chaussee 4
63457 Hanau
Germany
Phone +49 6181 59-13399
Fax +49 6181 59-2699
catalysts@evonik.com
evonik.click/catalysts