

## Product Information

# DYNOCEL® HG

Dynocel HG is a metal oxide promoted activated alumina for the removal of mercury to <10 ng/Sm<sup>3</sup> from vapor and liquid phase hydrocarbon streams.

## PRODUCT DESCRIPTION

Dynocel HG is a co-formed metal oxide promoted activated alumina for the removal of mercury from vapor or liquid phase hydrocarbon streams. The metal oxide promoter is distributed homogeneously throughout the adsorbent sphere providing uniform and predictable utilization of the Dynocel HG.

Dynocel HG offers high attrition resistance, high mechanical strength and high mercury adsorption capacity.

### Typical Properties

Property	Unit	Value
Abrasion Loss	wt%	2.0
Bulk Density	lb /ft <sup>3</sup>	46-50
Particle Size	in	1/16-1/8
Product Form		Spherical

The data represents typical values (no product specification)

## TYPICAL APPLICATIONS

Mercury removal to <10 nanograms/Sm<sup>3</sup> from vapor or liquid hydrocarbon streams such as LNG or natural gas.

## BENEFITS & ADVANTAGES

+Dynocel HG is a metal oxide promoted activated alumina for the removal of mercury to <10 nanograms/Sm<sup>3</sup> from vapor or liquid phase hydrocarbon streams.

+Dynocel HG has high mechanical strength with prevents alumina attrition over its life.

## HANDLING & PROCESSING

Dynocel HG may be handled in air.

## PACKAGING

2,000 lbs (907.2 kg) supersacks

350 lbs (158.5 kg) steel drums

## STORAGE

The material should be stored in its original container and in a dry, covered location protected from the ambient environment.

## SHELF LIFE

5 years in original packaging stored in a dry, covered location

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

### Evonik Operations GmbH

Catalysts  
Rodenbacher Chaussee 4  
63457 Hanau  
Germany  
Phone +49 6181 59-13399  
Fax +49 6181 59-2699  
catalysts@evonik.com  
evonik.click/catalysts