

Product Information

Durocel® 235

Inert bed support/tabular alumina grade spherical

PRODUCT DESCRIPTION

A highly inert tabular aluminum oxide for use in applications where chemical inertness, low porosity, low water absorption capacity and minimization of silica contamination are critical.

Typical Properties

Property	Unit	Value
Apparent Porosity	%	≤3.0
Bulk Density	lb /ft ³	126-133
Particle Size	- 50 mm	3 9.5 / 13 mm 37 mm
Side Crush Strength		176 (80) 360 (165) 440 (200) 1,323 (600) 2,645 (1,200) 3,307 (1,500)
Water Absorption	%	≤1.0

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Used as a catalyst and adsorbent bed support in refining, petrochemical and gas processing applications.

Product Composition

Product Composition	Unit	Value
Aluminum Oxide (Al ₂ O ₃) Content	wt%	99.5
Iron Oxide (Fe ₂ O ₃) Content	wt%	≤0.2
Sodium Oxide (Na ₂ O) Content	wt%	≤0.40
Silicon Dioxide (SiO ₂) Content	wt%	≤0.15

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

Physical characteristics yield excellent resistance to thermal and mechanical shock and abrasion.

High chemical purity and mechanical integrity result in one of the most inert support media available.

PACKAGING

25 kg (55.1 lb) sacks

1 MT supersacks

steel drums available

STORAGE

The material should be stored in its original container and in a dry, covered location protected from the ambient environment.

SHELF LIFE

5 years in original packaging stored in a dry, covered location

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Catalysts
Rodenbacher Chaussee 4
63457 Hanau
Germany
Phone +49 6181 59-13399
Fax +49 6181 59-2699
catalysts@evonik.com
evonik.click/catalysts