

Product Information

Dynasylan® DAMO

N-2-Aminoethyl-3-aminopropyltrimethoxysilane

CAS NUMBER

1760-24-3

PRODUCT DESCRIPTION

Dynasylan® DAMO is a diamino-functional silane which acts as an adhesion promoter between inorganic materials (for example glass, metals and fillers) and organic polymers (thermosets, thermoplastics and elastomers) and as a surface modifier.

Dynasylan® DAMO is a colourless to slightly yellowish liquid with an amine-like odour which is soluble in alcohols and aliphatic as well as aromatic hydrocarbons.

Typical Properties

Property	Unit	Value
Boiling Point, min. (20 hPa) DIN 51356	°C	140
Chemical Name		N-(2-Aminoethyl)-3-aminopropyltrimethoxysilane
Density (20 °C) DIN 51757	g/cm ³	~1.03
Flash Point, min. DIN EN ISO 2719	°C	136
Viscosity (20 °C) DIN 53015	mPa·s	~6

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dynasylan® DAMO is an important ingredient in many applications.

Examples are:

- glass fibre/glass fabric composites: as size constituent or finish
- glass and metal primers
- sealants and adhesives: as primer or additive
- mineral-filled polymers (composites): for pre-treatment of fillers and pigments or as additive
- paints and coatings: as additive and primer for improving adhesion to the substrate.

BENEFITS & ADVANTAGES

The most important effects which can be achieved using Dynasylan® DAMO are:

improvement in product properties, such as

- flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

improvement in processing properties, such as

- adhesion

DOSAGE

Processing:

For substrate pretreatments, e.g. as a primer (as an approx. 0.5-10 percent solution), Dynasylan® DAMO can advantageously be employed in organic solvents, such as alcohols and constituent of aqueous sizes or solutions. It may also be used as a pure substance or added to the polymer as an additive.

HANDLING & PROCESSING

Dynasylan® DAMO is a bifunctional organic compound in which the silicon-functional methoxy-groups hydrolyze in the presence of water to form reactive silanols, which can

be bonded to an inorganic substrate; the organophilic diamino group can interact with a suitable polymer.

The hydrolysis of Dynasylan® DAMO takes place autocatalytically. The pH of the hydrolysate is about 10-11. For longer stability of the hydrolysate a pH of 4 is recommended. Examples of particularly suitable inorganic substrates are glass or glass fibres. Examples of suitable polymers are PA, PBT, PC, EVA, modified PP, PVAC, PVC, acrylates and silicones.

Dynasylan® DAMO can undergo reactions with ketones or esters as solvents. The silane or silanized substrates can react with carbon dioxide to form the corresponding carbonates resp. carbamates. Product modifications are possible through addition reactions with suitable monomeric or polymeric compounds (for example isocyanates, epoxides, etc.).

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® DAMO is supplied in 25 kg, 200 kg drums and 950 kg IBC containers.

SHELF LIFE

In the unopened container Dynasylan® DAMO has a shelf life of min. 12 months from delivery.

Registration Listings

Registry	Status
Australia (AIC)	Yes
Canada (DSL)	Yes
China (IECSC)	Yes
EU (REACH)	Yes
EU (EINECS/ELINCS)	Yes
Japan (ENCS)	Yes
South Korea (KECL)	Yes
Philippines (PICCS)	Yes
USA (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects