

## Product Information

# Dynasylan® SILBOND® 40

## Ethyl polysilicates

### CAS NUMBER

confidential

### PRODUCT DESCRIPTION

Dynasylan® SILBOND® 40 is a clear, low-viscosity liquid with a minimum silica content of 40.0% (the Si content of Dynasylan® SILBOND® 40 is calculated as SiO<sub>2</sub>).

Dynasylan® SILBOND® 40 is an ethyl polysilicate that is the partially hydrolyzed product of tetraethyl orthosilicate (TEOS). The partial hydrolysis of TEOS (Si[OEt]<sub>4</sub>) results in the conversion of ethoxy groups to hydroxyl groups forming silanols. Subsequent condensation of silanols will form siloxane bonds (-Si-O-Si-O-) and eventually cause the material to gel.

Dynasylan® SILBOND® 40 is often used as an intermediate, which is further hydrolyzed to produce a binder that can be used for many applications. Several of these end-uses include inorganic zinc-rich primers, investment casting molds, cores and ceramic shapes, coatings, and thermal insulation.

## TYPICAL APPLICATIONS

Similar to Dynasylan® SILBOND® Condensed, Dynasylan® SILBOND® 40 is used to deposit silicic acid formed as a result of complete hydrolysis. The resulting silicic acid bonds well to many inorganic substrates, such as glass, ceramic, metal, fillers, pigments, and synthetic fibers. The deposition of a thin SiO<sub>2</sub> layer improves the chemical and thermal stability and mechanical properties.

Other applications are:

- binder, especially as Dynasylan® SILBOND® H- or HT-binders for inorganic zinc-rich coatings or precision investment castings
- encapsulant for hydroxyl poor fillers to enhance adhesion with functional silanes
- crosslinker component in cold-curing silicone rubber systems
- hardening component in dentistry for impression materials and as a binder for embedding material

Dynasylan® SILBOND® 40 is also used as starting material for sol-gel processes. It is usually used in conjunction with alkylsilanes (e.g. Dynasylan® MTES) organofunctional silanes and/or organic precursors (e.g. organic resins) to form siloxane networks. This makes it possible to obtain highly scratch-, abrasion-, and chemical-resistant coatings. Dynasylan® SILBOND® 40 is immiscible with water, therefore hydrolysis requires a cosolvent as a solubilizer. Mineral acids and ammonia are suitable as catalysts. Dynasylan® SILBOND® 40 or its hydrolysates are also the binder component for 1- and 2-pack inorganic zinc-rich coatings, for corrosion protection on steel, and for slurries used in precision investment castings.

### Typical Properties

Property	Unit	Value
<b>Appearance</b>		colorless, clear, liquid
<b>Boiling Point, min.</b> (1.013 hPa) OECD 103	°C	120
<b>Density</b> (20 °C) DIN 51757	g/cm <sup>3</sup>	-1.055-1.065
<b>Flash Point, min.</b> DIN EN ISO 13736	°C	30
<b>Viscosity</b> (20 °C) dynamic DIN 53015	mPa·s	5.0

The data represents typical values (no product specification)

### Product Composition

Product Composition	Unit	Value
<b>Silicon Dioxide (SiO<sub>2</sub>) Content</b> QC07106P	wt%	38-42

The data represents typical values (no product specification)

## HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

## PACKAGING

Dynasylan® SILBOND® 40 products could be available in pails, drums, totes and tanker quantities.

Please ask for further details.

## SHELF LIFE

In unopened container Dynasylan® SILBOND® 40 has a shelf life of min. 24 months from date of manufacture.

### Registration Listings

Registry	Status
Australia (AIC)	Yes
Canada (DSL)	Yes
China (IECSC)	Yes
EU (REACH)	Yes
Japan (ENCS)	Yes
South Korea (KECL)	Yes
New Zealand (NZIoC)	Yes
Philippines (PICCS)	Yes
Taiwan (TCSI)	Yes
United States of America (TSCA)	Yes

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

### Evonik Operations GmbH

Smart Effects  
Rodenbacher Chaussee 4  
63457 Hanau  
Germany  
[ask-se@evonik.com](mailto:ask-se@evonik.com)  
[ask-se-asia@evonik.com](mailto:ask-se-asia@evonik.com)  
[ask-se-america@evonik.com](mailto:ask-se-america@evonik.com)  
[www.evonik.com/smarteffects](http://www.evonik.com/smarteffects)