

Product Information

# Dynasylan® SIVO CLEAR EC

Coating System for Oil-, Water-, and Dirt-Repellent Treatment of Smooth Inorganic Surfaces

## CAS NUMBER

confidential

## PRODUCT DESCRIPTION

Dynasylan® SIVO CLEAR EC is a one-component user-friendly coating system for smooth surfaces such as glass and glazed ceramic.

### Typical Properties

Property	Unit	Value
<b>Chemical Name</b>		1-component ready-for-use, proprietary fluorosilane composition
<b>Density</b> (20 °C) DIN 51757	g/cm <sup>3</sup>	0.79
<b>Flash Point, min.</b> DIN 51755	°C	12.5
<b>Viscosity</b> (20 °C) DIN 53015	mPa·s	2.5

The data represents typical values (no product specification)

## TYPICAL APPLICATIONS

The consumption Dynasylan® SIVO CLEAR EC depends on the application method, mostly about 30 - 50 ml/m<sup>2</sup> are sufficient.

Product Properties and Benefits to the User

Treatment of windshields:

- Better visibility in the rain, particularly on throughways and rural roads
- In winter: obviates time-consuming de-icing
- In summer: insect splatter easier to remove

Easy-to-clean glass components of shower stalls, sanitary ceramics:

- Lime and soap residues easy to remove
- Aggressive cleaning agents are not needed. A wet cloth is generally sufficient.

Easy-to-clean surfaces on other glass objects (e.g. greenhouses, canopies, skylights, etc.):

- The cleaning cycle is extended.
- Less cleaning agent is needed.
- Dirt is easier to remove.

Use on Smooth Inorganic Surfaces (e.g. Glass, Ceramic)

Application Procedure:

- Do not apply the product at temperatures below 10 °C!
- Do not expose surfaces to be treated to sunlight!
- Make sure that the surface is not hot.
- Provide adequate ventilation and fresh air!

Before application the surface has to be cleaned! The optimum temperature for the treatment is 15-25 °C.

## DOSAGE

Step 1: Cleaning the Surface

In order to permit sufficient chemical bonding of Dynasylan® SIVO CLEAR EC to the substrate, the surfaces have to be carefully cleaned before the application. The long-term stability and abrasion resistance of the coating

depends on how well Dynasylan® SIVO CLEAR EC is chemically bonded.

The surfaces to be treated can be cleaned with a commercial glass cleaner. After that they should be polished until the surface is dry. For an optimum pre-treatment of the surface, especially for automotive glass, we recommend an abrasively cleaning with a 30 % aqueous cerium oxide\* slurry. The slurry should be shaken thoroughly before use. The cerium oxide slurry can be applied with a cotton cloth or paper towel and should be polished uniformly as a thin liquid film for several minutes. Subsequently, the film is allowed to dry.

\* Supplier: Cerium oxide, 99% pure (corn size 2-3 mm);

Lehmann&Voss&Co., Alsterufer 19 20354 Hamburg

#### Step 2: Treatment Process

Direct exposure to sunlight during application should be avoided. In the case of windshield treatment, the two halves of the windshield (left/right) should be treated one after the other. A certain amount of the Dynasylan® SIVO CLEAR EC is applied as a thick liquid film and should be polished quickly and uniformly with paper towel for at least ½ -1 minutes. In case the solvent evaporates before it has been uniformly polished in, more product needs to be applied. Do not let the film dry sporadically. Before the liquid film dries, excess Dynasylan® SIVO CLEAR EC should be polished off with a clean paper cloth. Residues of dried formulation and grey streaks can be polished off completely using a clean piece of paper towel. Persisting residues can be polished off completely using a small amount of Dynasylan® SIVO CLEAR EC and a clean paper cloth. After application the coating should be air dried for about 30 minutes. In the case of windshield treatment please do not use the wipers during this time. A hydrophobic effect generally can be seen depending on the substrate, reactivity and temperature after about 5–15 min and is further enhanced after a few minutes. Renewing Already Coated Glass Surfaces The coating with Dynasylan® SIVO CLEAR EC is long-lasting. Once the effects wear off, the surface can be re-coated. For a re-coating the cleaning with cerium oxide and the application of Dynasylan® SIVO CLEAR EC are done in the same way as the first treatment. If the glass was treated with a different coating before, repeated treatment with an abrasive cleaner is vital. Special note to polishing cloths Do not use microfibre or cotton cloths for the

polishing of Dynasylan® SIVO CLEAR EC in Step 2. Recommendation for polishing cloths: Multitex white or blue viskose cloths from ZVG-Zellstoff-Vertriebs-GmbH. Wypall X60 / Kimnet cloths – Quarter Fold Pack Code 6034 from KIMBERLY-CLARCK Professional (USA) (paper cloths 36,5 x 31,5 cm) For further information please write to [dynasylan@evonik.com](mailto:dynasylan@evonik.com)

## HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

## PACKAGING

Dynasylan® SIVO CLEAR EC is delivered in PE cans (20 kg), steel drums with plastic linings (150 kg) and IBC's (750 kg).

## SHELF LIFE

In originally sealed containers Dynasylan® SIVO CLEAR EC has a shelf life of min. 12 months from delivery.

### Registration Listings

Registry	Status
Australia (AIIC)	No
Canada (DSL)	Information on Request
China (IECSC)	Information on Request
European Union (EINECS/ELINCS)	Yes
Japan (ENCS)	Yes
South Korea (KECL)	No
Philippines (PICCS)	No
United States of America (TSCA)	No

#### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

#### Evonik Operations GmbH

Smart Effects  
Rodenbacher Chaussee 4  
63457 Hanau  
Germany  
ask-se@evonik.com  
ask-se-asia@evonik.com  
ask-se-america@evonik.com  
[www.evonik.com/smarteffects](http://www.evonik.com/smarteffects)