

Product Information

Dynasylan® SIVO CLEAR SET K1

- **Component 1 - Dynasylan® SIVO CLEAR is a 2-component system for hydro- and oleophobic treatment of e.g. glass and ceramic surfaces. Each component has its own material safety data sheet.**

CAS NUMBER

confidential

PRODUCT DESCRIPTION

Dynasylan® SIVO CLEAR is a user-friendly 2-component coating system for smooth surfaces such as glass.

The right amount of formulation is achieved by mixing the two components 1:1 (by volume). This total formulation is ready for application after about 3 minutes of shaking or stirring. It should be used within 1 day. This gives the user flexibility in designing the working steps and prevents waste. The consumption of the ready-to-use solution depends on the application method, mostly about 50 ml/m² are sufficient.

Typical Properties

Property	Unit	Value
Density (20 °C) DIN 51757	g/cm ³	0.8
Flash Point, min. DIN EN ISO 13736	°C	7
Viscosity (20 °C) DIN 53015	mPa·s	2

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Treatment of windshields:

- Better visibility in the rain, particularly on throughways and rural roads
- In winter: obviates time-consuming de-icing
- In summer: insect splatter easier to remove

BENEFITS & ADVANTAGES

Easy-to-clean glass components of shower stalls, sanitary ceramics:

- Lime and soap residues easy to remove
- Aggressive cleaning agents are not needed. A wet cloth is generally sufficient

Easy-to-clean surfaces on other glass objects (e.g. greenhouses, canopies, skylights, etc.):

- The cleaning cycle is extended
- Less cleaning agent is needed
- Dirt is easier to remove

DOSAGE

Do not apply the product at temperatures below 10 °C! Do not expose surfaces to be treated to sunlight! Make sure that the surface is not hot. Provide adequate ventilation and fresh air!

Step 1: Mixing the Coating Formulation

Mixing of the formulation at room temperature is recommended. Before treating the surface, Dynasylan® SIVO CLEAR K2 should be mixed with Dynasylan® SIVO CLEAR K1 1:1 (by volume, e.g. 2 x 50 ml). The obtained formulation should be shaken for a minimum of 3 minutes. After that the solution is ready to use, and has to be used within 1 day. Before the application of this mixture, the substrate has to be cleaned. Meanwhile keep the mixture unstirred. The temperature during processing should be in the range of 10 °C - 30 °C, preferably 15 - 25 °C.

Step 2: Cleaning the Surface

In order to permit sufficient chemical bonding of Dynasylan® SIVO CLEAR to the substrate, the surfaces have to be carefully cleaned before the application. The long-term stability and abrasion resistance of the coating depends on how well Dynasylan® SIVO CLEAR is chemically bonded.

The surfaces to be treated can be cleaned with a commercial glass cleaner. After that they should be polished until the surface is dry. For an optimum pretreatment of the sur-

face, we recommend an abrasively cleaning with a 30 % aqueous cerium oxide* slurry. The slurry should be shaken thoroughly before use. The cerium oxide slurry can be applied with a cotton cloth or paper towel and should be polished uniformly as a thin liquid film for several minutes. Subsequently, the film is allowed to dry. The dried cerium oxide is wiped off with a clean, dry paper cloth (it may have to be repolished several times with a new paper cloth). The cerium oxide should be completely removed. The abrasive cleaning ensures a completely clean and reactive glass surface. Just after the abrasive cleaning, the surface should be coated.

Step 3: Treatment Process

Direct exposure to sunlight during application should be avoided. In the case of windshield treatment, the two halves of the windshield (left/right) should be treated one after the other. A certain amount of the Dynasylan® SIVO CLEAR formulation obtained in step 1 is applied as a thick liquid film and should be polished quickly and uniformly with a paper towel for at least ½ -1 minutes. In case the solvent evaporates before it has been uniformly polished in, more formulation needs to be applied. Do not let the film dry sporadically. Before the formulation dries, excess solution should be polished off with a clean paper cloth. Residues of dried formulation and grey streaks can be polished off completely using a clean piece of paper towel. Persisting residues can be polished off completely using a small amount of Dynasylan® SIVO CLEAR formulation and a clean paper cloth. A hydrophobic effect generally can be seen depending on the substrate, reactivity and temperature already after about 5–15 min and is further enhanced after a few minutes. Anyhow it is recommended to let the coating dry for at least 30 minutes. In the case of windshield treatment please do not use the wipers during this time. Renewing Already Coated Glass Surfaces The coating with Dynasylan® SIVO CLEAR is long-lasting. Once the effects wear off, the surface can be re-coated. For a re-coating the cleaning with cerium oxide and the application of Dynasylan® SIVO CLEAR are done in the same way as the first treatment. If the glass was treated with a different coating before, repeated treatment with an abrasive cleaner is vital.

HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

The two-component product Dynasylan® SIVO CLEAR is delivered in two separate steel drums with plastic linings (2 x 25 l, 2 x 180 l).

STORAGE

The mixed formulation must be used within 1 day. For further information please write to dynasylan@evonik.com

SHELF LIFE

In the originally sealed containers Dynasylan® SIVO CLEAR K1 and K2 has a shelf life of min. 12 months from delivery.

Registration Listings

Registry	Status
Australia (AIIC)	Yes
Canada (DSL)	No
China (IECSC)	Yes
European Union (EINECS/ELINCS)	Yes
Japan (ENCS)	No
South Korea (KECL)	Yes
Philippines (PICCS)	No
United States of America (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
 Rodenbacher Chaussee 4
 63457 Hanau
 Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects