

Product Information

Dynasylan® 1122

Bis(3-triethoxysilylpropyl)amine

PRODUCT DESCRIPTION

Dynasylan® 1122 is a secondary aminofunctional ethoxysilane possessing two symmetric silicone atoms. Dynasylan® 1122 acts as an adhesion promoter between inorganic materials (for example glass, metals and fillers) and organic polymers (thermosets, thermoplastics and elastomers), as a surface modifier and can be used for the chemical modification of substances.

Dynasylan® 1122 is a colourless to yellow liquid with an amine-like odor which is, for example, soluble in alcohols, aliphatic or aromatic hydrocarbons.

Dynasylan® 1122 is a bifunctional organic compound in which the silicon-functional ethoxy-groups hydrolyze in the presence of water to form reactive silanols, which can be bonded to an inorganic substrate; the organophilic amino group can interact with a suitable polymer. Due to 6 hydrolyzable substituents present in one molecule, Dynasylan® 1122 is exceptionally suitable to form highly crosslinked networks on and between substrates and in organic matrices.

The hydrolysis of Dynasylan® 1122 in water takes place by acidic catalysis (e.g. formic or acetic acid at a pH of 2-3). In order to achieve solubility in organic solvents simply add 2-4 wt.-% of water per wt.-% of Dynasylan® 1122. Upon stirring for 5h the solutions are ready for use.

Examples of suitable inorganic substrates are glass, glass fibres, glass wool, mineral wool, silicic acid, quartz, sand, cristobalite, wollastonite and mica; also suitable are aluminium hydroxide, kaolin, talc, other silicate fillers, metal oxides and metals. Examples of suitable polymers are epoxy resins, polyurethanes, phenolic resins, furan resins, melamine resins, PA, PBT, PC, EVA, modified PP, PVB, PVAC, PVC, acrylates and silicones.

The secondary amino group in Dynasylan® 1122 provides high basicity at somewhat lower reactivity compared to primary amino groups. This is of major advantage in e.g. adhesives and sealants where the silane is added to the polymer matrix: Homogeneous distribution and bonding/networking of Dynasylan® 1122 to the inorganic filler can

commence unless bonding to organic materials (e.g. polymers) will proceed.

Moreover, Dynasylan® 1122 has been successfully used as a component in aqueous PA- and PU-sizes for glass fibers.

Typical Properties

| Property | Unit | Value |
|--|-------------------|-------------------------------------|
| Apparent Porosity | | N/A |
| Boiling Point (1013 hPa) ASTM D-1120 | °C | ≤300 |
| Chemical Name | | N,N-bis-3-triethoxysilylpropylamine |
| Density (20 °C) DIN 51757 DIN EN ISO 2719 | g/cm ³ | ~0.964-0.972 |
| pH Value (1.0 g/l) DIN EN ISO 10523 | | ~10.2-10.8 |
| Product Purity, min. wt.-% SAA 0719 | % | 96 |
| Viscosity (20 °C) DIN 53015 | mPa·s | ~3-10 |

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dynasylan® 1122 is an important additive in many applications.

Examples are:

- glass fiber/glass fabric composites: as size constituent or finish
- metal primers
- mineral fiber insulating materials, abrasives: as additive to phenolic resin binders
- foundry resins: as additive to phenolic, furane and melamine resins
- adhesives and sealants: as primer or additive
- mineral-filled polymers (composites) or HFFR cables: for pretreatment of fillers and pigments
- paints and coatings: as additive and primer for improving adhesion to the substrate

BENEFITS & ADVANTAGES

The most important effects which can be achieved using Dynasylan® 1122 are:

improvement in product properties, such as

- flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

improvement in processing properties, such as

- adhesion
- filler dispersion
- rheological behaviour: reduction in viscosity, Newtonian behaviour
- higher degree of filling

HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® 1122 is supplied in 25 kg PE cans and in 180 kg drums.

STORAGE

It is recommended to store Dynasylan® 1122 above 0 °C, because of the viscosity change at low temperatures.

SHELF LIFE

In the originally sealed containers Dynasylan® 1122 has a shelf life of min. 12 months from delivery.

Registration Listings

| Registry | Status |
|---------------------|------------------------|
| Australia (AIIC) | No |
| Canada (DSL) | Information on Request |
| China (IECSC) | Yes |
| EU (EINECS/ELINCS) | Yes |
| UK (UK-REACH) | Yes |
| Japan (ENCS) | Information on Request |
| South Korea (KECL) | Yes |
| Philippines (PICCS) | Yes |
| USA (TSCA) | Yes |

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects