

Product Information

Dynasylan® MTMO

3-mercaptopropyltrimethoxysilane; MPTMS

PRODUCT DESCRIPTION

Dynasylan® MTMO is a bifunctional organosilane possessing a reactive organic mercapto and a hydrolyzable inorganic methoxysilyl group.

The dual nature of its reactivity allows Dynasylan® MTMO to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers), thus functioning as an adhesion promoter, crosslinking agent, surface modifier or reactive reagent.

Dynasylan® MTMO is a clear, colorless to light yellow liquid with a slightly mercaptan odor. It is soluble in alcohols, ketones and aliphatic or aromatic hydrocarbons.

Typical Properties

Property	Unit	Value
Apparent Porosity		N/A
Boiling Point (4 hPa) DIN 51751	°C	≤85
Chemical Name		3-Mercaptopropyltrimethoxysilane; MPTMS
Density (20 °C) DIN 51757 (20, D) DIN 51423	g/cm ³	1.06
Viscosity (20 °C) DIN 53015	mPa·s	2.0-2.0

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dynasylan® MTMO is used in applications such as:

- adhesives and sealants: as a primer, additive, or for chemical modification of the polymer
- glass composites: as a finish or a size ingredient
- glass and metal primer
- mineral filled polymers: for pretreatment of fillers and pigments or as an additive
- crosslinking of polymers

BENEFITS & ADVANTAGES

Important product effects that can be achieved through the use of Dynasylan® MTMO include:

- Improved adhesion profiles in adhesives and sealants to appropriate substrates, especially to metals
- Compression set
- Improved mechanical properties, e.g. flexural strength, tensile strength, impact strength and modulus of elasticity, tear strength
- Improved moisture and corrosion resistance
- Improved electrical properties, e.g. dielectric constant, volume resistivity
- Increased thermal resistivity

Dynasylan® MTMO can also improve such processing properties as:

- cure time
- adhesion
- filler dispersion
- rheological behavior: (e.g. viscosity reduction)
- higher filler loading

DOSAGE

Dynasylan® MTMO can be used as a primer (i.e. a ca. 0.5-10 wt.% solution in an organic solvent such as alcohol), as an ingredient in a solution, or neat. A chemical modification can be achieved by reaction of Dynasylan® MTMO with suitable functional monomers or polymers.

HANDLING & PROCESSING

In the presence of water, the methoxy groups of Dynasylan® MTMO hydrolyze and form reactive silanol groups which can bond to a variety of inorganic substrates. The organophilic mercapto end of Dynasylan® MTMO can react with a suitable polymer. Hydrolysis of Dynasylan® MTMO is catalyzed by acids.

Examples of suitable inorganic substrates are glass, glass fibers, silica, quartz, sand, cristobalite, mica kaolin, talc, other silicate fillers and metals. Dynasylan® MTMO may be used with such polymers as polyurethanes, polysulfides, sulfur-cured and metal oxide-cured elastomers.

Product modifications are possible by using Dynasylan® MTMO in addition or grafting reactions with suitable monomers or polymers (e.g. isocyanates, PVC etc.). An Si-O-Si crosslinking can take place via the silicon functional groups of the silane.

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® MTMO is supplied in 25 kg and 200 kg drums and 1.000 kg containers.

SHELF LIFE

In the unopened container Dynasylan® MTMO has a shelf life of min. 12 months from delivery.

Registration Listings

Registry	Status
Australia (AIIC)	Yes
Canada (DSL)	Yes
China (IECSC)	Yes
EU (REACH)	Yes
EU (EINECS/ELINCS)	Yes
Japan (ENCS)	Yes
South Korea (KECL)	Yes
Philippines (PICCS)	Yes
USA (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects