

Product Information

Dynasylan® MTMS

Methyltrimethoxysilane

PRODUCT DESCRIPTION

Dynasylan® MTMS, an alkyltrialkoxysilane is an important component in sol-gel systems.

Dynasylan® MTMS is a colorless, low-viscosity liquid. Dynasylan® MTMS is regarded as trifunctional since all three alkoxy groups are able to hydrolyze. Additionally Dynasylan® MTMS contains a methyl group that adds organic character to the products. Hydrolysis leads to silanol groups which, in a subsequent condensation reaction, form very stable siloxane bonds (-Si-O-Si-). Condensation occurs parallel to hydrolysis once a certain amount of silanol groups have been formed. The absolute and relative rates of hydrolysis and condensation depend on a number of factors. The most important factors include pH, concentration, solvent, temperature and the catalyst.

Typical Properties

Property	Unit	Value
Appearance		colorless liquid
Boiling Point, min. (1.013 hPa) DIN 51751	°C	102
Chemical Name		Methyltrimethoxysilane
Density (25 °C) DIN 51757	g/cm ³	0.95
Flash Point, min. DIN EN ISO 13736	°C	11
Viscosity (25 °C) DIN 53015	mPa·s	0.5

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Dynasylan® MTMS reacts faster with water than Dynasylan® MTES. In some sol-gel applications Dynasylan® MTMS is partially hydrolyzed to form a pre-product that can be further crosslinked using temperature. This prehydrolysis often is done in conjunction with other

organofunctional silanes (e.g. Dynasylan® GLYMO), silicic acid esters or even an aqueous silica sol. This preproduct can be modified even further by addition of organic resins or inorganic nanoparticles such as AEROSIL®.

BENEFITS & ADVANTAGES

It is also possible to construct an inorganic/organic network by adding silanes containing organofunctional groups (e.g. aminopropyl groups) and organic resins and polymerizing using standard organic methods. This principle makes it possible to obtain mar resistant coatings having a higher UV-stability than traditional organic coatings. This can also lead to more flame resistant materials than using traditional resins.

HANDLING & PROCESSING

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use.

The Safety Data Sheet is available on our website <https://silanes.evonik.com/en> or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

PACKAGING

Dynasylan® MTMS are available in 190 kg drums

Pails (25 kg) are available 12 weeks lead time.

STORAGE

Dynasylan® MTMS must be stored with exclusion of moisture.

SHELF LIFE

In originally sealed containers, Dynasylan® MTMS has a shelf life of min. 12 months from delivery.

Registration Listings

Registry	Status
----------	--------

Australia (AIC)	Yes
-----------------	-----

Canada (DSL)	Yes
--------------	-----

China (IECSC)	Yes
---------------	-----

EU (REACH)	Yes
------------	-----

EU (EINECS/ELINCS)	Yes
--------------------	-----

Registration Listings

Registry	Status
----------	--------

Japan (ENCS)	Yes
--------------	-----

South Korea (KECL)	Yes
--------------------	-----

Philippines (PICCS)	Yes
---------------------	-----

USA (TSCA)	Yes
------------	-----

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Smart Effects
Rodenbacher Chaussee 4
63457 Hanau
Germany
ask-se@evonik.com
ask-se-asia@evonik.com
ask-se-america@evonik.com
www.evonik.com/smarteffects