

Product Information

Octolyst® 1700

Nickel on Alumina Fixed Bed Catalyst

PRODUCT DESCRIPTION

Octolyst® 1700 is a highly active nickel on alumina catalyst. With designed shape and low-content Nickel, these tablets can be operated in ammonia cracking with excellent performance.

Typical Properties

Property	Unit	Value
Appearance		Black tablets
Bulk Density	g/cm ³	1.4
Particle Size		3.5 mm x 3.5 mm
Side Crush Strength		>100 N/particle

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Ammonia cracking

Product Composition

Product Composition	Unit	Value
Nickel (Ni) Content	%	≤18.5

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

- superior reactivity and selectivity
- high mechanical stability
- development of tailor-made catalysts in the context of an exclusive project possible

HANDLING & PROCESSING

Activation: The catalyst will be delivered in oxidized state. Reduction with hydrogen or hydrogen containing gas is necessary to activate the catalyst. An activation procedure is available on request

Typical Operating Conditions:

NH₃ GHSV: 500-30,000 1/h

Pressure: Ambient - 5 MPa

Temperature: 600 - 800 °C

Sampling will be made under sample name CPC SP1700

PACKAGING

Octolyst® is supplied in 210 liter steel drums, net weight is approx. 250 kg

STORAGE

Drums should be stored in a dry place, not be exposed to direct sunlight and be protected from freezing.

SHELF LIFE

Subject to the appropriate storage conditions, the shelf life of Octolyst® catalysts in sealed original drums is > 3 years from date of shipment.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Catalysts
Rodenbacher Chaussee 4
63457 Hanau
Germany
Phone +49 6181 59-13399
Fax +49 6181 59-2699
catalysts@evonik.com
evonik.click/catalysts