#### **Product Information**

# Peroxcel® 836

Activated alumina for purification of hydrogen peroxide working solutions.

#### **PRODUCT DESCRIPTION**

Activated alumina for purification of hydrogen peroxide working solutions.

Typical Properties		
Property	Unit	Value
BET Surface Area	m²/g	340
Bulk Density	lb /ft³	40
Macroporosity	ml/g	0.18
Particle Size		8x14 mesh

The data represents typical values (no product specification)

# **TYPICAL APPLICATIONS**

Production of hydrogen peroxide

Product Composition	Unit	Value
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ) Content	wt%	99.6

## **BENEFITS & ADVANTAGES**

Activated alumina for purification of hydrogen peroxide working solutions.

#### **PACKAGING**

2,000 lbs (907.2 kg) supersacks, steel drums available

#### **STORAGE**

The material should be stored in its original container and in a dry, covered location protected from the ambient environment.

### **SHELF LIFE**

5 years in original packaging stored in a dry, covered location

#### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

#### Evonik Operations GmbH

Catalysts Rodenbacher Chaussee 4 63457 Hanau Germany Phone +49 6181 59-13399 Fax +49 6181 59-2699 catalysts@evonik.com evonik.click/catalysts

