

Product Information

VESTOPLAST® 408

VESTOPLAST® 408 is a hard grade with excellent thermal stability under load and tear strength.

PRODUCT DESCRIPTION

Free flowing granules. High crystallinity.

Low viscosity and high softening point and high S.A.F.T.

Hardest grade with high tear strength.

Excellent foamability.

Resistant against battery acid (37% sulfuric acid).

Typical Properties

Property	Unit	Value
Chemical Name		Amorphous Poly-alpha-olefin (APAO)
Melt Viscosity at 190°C according to DIN 53019	mPa·s	8000
Needle Penetration DIN EN 1426	0.1 mm	5
Open Time Evonik method	sec	65
Softening Point DIN EN 1427	°C	118

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

Raw material

- for the production of hot melts, e.g. for the textile-, paper- and packaging and woodworking industry
- air filter: automotive-, industrial-, and HEPA- filters
- filter pleating
- lead acid batteries: fixation of plates
- foamable
- gap filling applications

DOSAGE

We are pleased to send guideline formulations.

HANDLING & PROCESSING

In case of thermal processing, provide for extraction of the vapours or adequate ventilation. Fumes from hot processing may be irritating to eyes and respiratory tract.

PACKAGING

- 20 kg bags on CP4 palette of 1000kg

Bags made of recyclable polyethylene (LDPE, Resin Identification Code: 04).

STORAGE

Store in a dry, cool, and well-ventilated place. General rules of fire prevention should be observed.

Keep away from sources of ignition - No smoking.

SHELF LIFE

3 years

HAZARDOUS SUBSTANCE

No hazardous substance

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Oxeno GmbH & Co. KG

Paul-Baumann-Straße 1
45772 Marl
Germany
C4-chemicals@evonik.com
[evonik.click/c4-chemicals](https://www.evonik.com/c4-chemicals)