

TEGO® Variplus 1201 TF NPA

DESCRIPTION

TEGO® Variplus 1201 TF NPA strongly improves mechanical properties of solventborne inks and coatings. It enhances gloss, blocking resistance, and adhesion on many substrates.

KEY BENEFITS

- very good adhesion on plastics
- improves gloss, hardness, blocking resistance
- high light and heat resistance

EFFECT

Hardness



Gloss



Viscosity reduction / increase of solids content



Pigment wetting and stabilization



Adhesion improvement (e.g. metal, plastics)



SUITABILITY

waterborne



solventborne



radiation-curing



pigmented coatings



clear coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Wood coatings
- Plastic coatings
- Pigment concentrates
- Printing Inks

TECHNICAL DATA

active matter content	48 %
appearance	clear liquid
chemical description	polyurethane polyol resin
glass transition temperature	Approx. 130 °C
hydroxy value (calculated on non-volatile content)	Approx. 200 mg KOH/g
solvent	n-Propylacetate

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied on total formula weight: 5 - 20 %

PROCESSING INSTRUCTIONS

- Addition to the coating as supplied.
- Addition to the grind or during the let-down is possible.

HANDLING & STORAGE

When stored in an original unopened packaging the product has a shelf life of 48 months from the date of manufacture. The product should be stored out of direct sunlight.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com